

Firestone
PLASTICS COMPANY



FPC
VINYL COMPOUNDS

FPC 1379

Typical Physical Properties*

<u>Characteristic</u>	<u>Test Method</u>	<u>Value</u>
Specific Gravity	ASTM D-792-66	1.36
Hardness, Shore Durometer Instantaneous	ASTM D-2240-75	70A
Tensile Strength, psi	ASTM D-412-68	1490
Modulus at 100% Elongation, psi	ASTM D-412-68	670
Ultimate Elongation %	ASTM D-412-68	290
Brittleness Temperature °C	ASTM D-746-73	-37

*75 Mil Plaque Data

Recommended Extrusion Temperature: 340-350°F

Classification: ASTM D-2287-70 Type PVC 3530600

Compound Characteristics: Filled, Opaque

Colors: Natural, Black, Gray

Recommended Application: Profile Extrusion

NON WARRANTY. The information presented in this publication is based upon the research and experience of Firestone and is to the best of its knowledge accurate; however, no guarantee of its accuracy is made. Since Firestone has no control over the conditions under which its products may be employed; and since information as to the physiological and other properties of its products is incomplete, Firestone cannot guarantee the results obtained and assumes no liability whatsoever for possible damage or injury whether or not caused by following the suggestions in this brochure. Firestone will not be liable for resulting or consequential damage. Firestone warrants that none of its commercial products infringes the claims of any United States patent but no license is granted nor recommendation made hereby to practice any invention covered by any patent owned by Firestone or by others.

UCC
040233