DISCONTINUED

GOODS	Endurance Tint Base	LABORATORY NO.	
CONSISTENCY		COST CLASS.	DATE **9/26/5
FOR USE ON	**Destroy formula dated 9/4/56 SEE	STRAINER	GRIND 3-4
CUSTOMER	10-8-56	MILL Pebble or	WT. OR BE 13.6

CODE NUMBER	ONE GALLON BATCH PINTS	LBS.	OZS.	LARGE BATCH GALS.	LBS.	OZS.
W-180		5			350	
W-33		3	11		260	
W-63		2	12		195	
W-195			1		4-1/2	
O-286	1-1/2			13		
O-62	1/4			2-1/4		
O-1	4-3/8			38-1/2		
S-43	1-3/8			12		
S-148	1/2			4-1/2		
VM-432			2 Loz.	1-1/8		
VM-523			1 Loz.	1/2		
VM-433			5/16 Loz.			22 Loz
S-72 or S-91			1/2 Loz.			35 Loz
APA Puffing Agent (hold) as needed.				1/8 or 1/4 gals./100 gals.		
YIELD	1.42			100		

IS AGITATOR REQUIRED XXXX Hi-R
VISC. F.B. 85-90 KU TEMP.
VISC. RED. TEMP.
VISCOSIMETER Stormer
COLOR SHEEN
NON VOL. FLASH PT.
MATCH FOR
REDUCER S-43
AMT. FOR BRUSHING As needed
SPRAYING TUMBLING
DIPPING DRIP TIME
BAKE TEMP.
AIR DRIES IN O.N.
A. D. TO RECOAT IN 72 hrs.
REMARKS: Changed for lower cost.

FORMULATOR J.E. Southwick
26-8-8

Standard Formula. Not to be taken from File.

N12028

GLD058970

COST	DATE	ANALYSIS		CUSTOMERS Y-1804-U
		PIGMENT 59 %		Endurance Tint Base
		VEHICLE 41 %		
		100 %		"Y" Trade Sales List 10-8-[illegible]
		PIGMENT		Ecuador 2-16-57
		Titanium Calcium	43%	
		Zinc Oxide	32	Bradley (Ecuador) [illegible]
		Calcium Carbonate	25	[illegible]
			100%	
				No change in analysis.
				Drees 7-15-57
				Portland via S. Fran 6-17-[illegible]
				Chile 10-16-58
		VEHICLE		West Indies 11-24-[illegible]
		Raw Linseed Oil	55%	West Indies 1-19-59
		Bodied Linseed ~~Ink~~ Oil	22	Paul Hawkins 7-19-60
		~~Nuberak Spirits & Driers~~	23	
		Mineral Spirits & Driers	100%	
		Y-1804	659	

GLD058971