Aroclor 1242 Lot #L-422 (Plant B)
(Sample Taken from Columns) (2-24-69)

	Dissipation Factor after 30 mins.	Resistivity (500 Volts)
Unwashed bottle	.00072	81×10^{12}
Washed bottle	.00042	100×10^{12}

0080284