MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Y7808 LOT 33686

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
	18	2348	4-62	
	STUMP		2313	

TOTAL NET WT. 2348 PKG. N-CODE

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	1/10/80	23

DUP050293365



DUP050293366

N33122.01

33/106

CG 46 CODE YT-808-D PKG. ____

→ JAN-7 33686

EST. WGT. ~~2238~~ 2573 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
YT-808-D (D)	EWK 9/28/77
	BBK 10/17/77
	DCG 10/17/77
TYPED BY	
jlc 10/26/77	

MAKING NOTES

REMARKS

NAME: DALAMAR® YELLOW

BLEEDING

-PRESSING-

INSTRUCTIONS						RECORD					
VAT		106				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		1-7-80				STARTED	7 30 pm				
TIME		6 40 P				CAKES USED	6				
RELEASED BY		[illegible]				WATER ON	11 pm				
PRESS	32	33	35			HRS. WASHED	4 HRS				
NO. OF CAKES	60	68	60			OHMS	4000				
PRESS	WITHOUT	AGITATION				HRS. WASHED					
WASH TO	4000	OHMS with 35-75°F water				OHMS					
TEST AFTER	4	HOURS				HRS. WASHED					
LOAD	on 9 cars					OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	6				
						EXPLAIN LOSSES					

SAMPLES

DELIVER TO

SAMPLED BY RELEASED BY

-DRYING-

DRY 24 HOURS AT 200°F

TEMP.

LUMP: - OK - WET - SALTS - CONTAMINATED

No record of any processing losses [illegible]

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 14

SAMPLES

NO. CARS PULLED

LUMP WGT. 2313

DELIVER TO

SAMPLED BY

RELEASED BY

-GRINDING-

MILL 4 or 10 HSP 1/8"RB SCREEN 3500 RPM

MAX. TEMP. 190 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

1-10-80

SAMPLE WITHOUT MIXING

SAMPLES 1 env + 1 Pint can

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050293367

N33122.02



DUP050293368

N33122.03