MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE RT-539 LOT 3C312


NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	5	500	37	
	STUMP	Dump	514	

TOTAL NET WT. 500 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

8/1/ 16C

DUP050106733



DUP050106734

12/200

CG 40 CODE RT-539-D PKG.

→ JU'2[illegible] 36312

EST. WGT. 486 LBS.

2 gs

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
RT-539-D (N)	EWK 10-25-77
	DCG 10-25-77
TYPED BY	
jlc 11-15-77	

MAKING NOTES

REMARKS

NAME: NAPHTHANIL® RED DARK

[illegible] BLEEDING

INSTRUCTIONS

VAT	260
DATE	7/1/80
TIME	3:50 PM
RELEASED BY	[illegible]
PRESS	12
NO. OF CAKES	36
PRESS	WITHOUT AGITATION
WASH TO	4000 OHMS WITH 35-75°F WATER
TEST AFTER	4 HOURS
LOAD	ON 3 CARS

SAMPLES

DELIVER TO

-PRESSING- RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	8				
CAKES USED	36				
WATER ON	[illegible]				
HRS. WASHED	5				
OHMS	4000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	3				

EXPLAIN LOSSES

SAMPLED BY RELEASED BY

-DRYING-

RECORD DRY 20 HRS AT 180°F. M. N.V.

TEMP. °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS: 5

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT. 5/4

SAMPLED BY RELEASED BY

-GRINDING-

MILL #5 LSP 1/8" RP SCREEN 1750 RPM

MAX. TEMP. 170 °F

SAMPLE AFTER WITHOUT MIXING

SAMPLES 1 Env

DELIVER TO C T L

SCREEN	RPM
MAX. TEMP.	°F

EXPLAIN LOSSES

DATE MIXED 8/1/80

SAMPLED BY 213 RELEASED BY

DUP050106735

36312
51
16

0.00 *

WET PAN

1.45 +
0.14 -
1.37 +
0.14 -
1.31 +
0.14 -
1.06 +
0.14 -
4.63 *

4.63 +
0.65 +
0.14 -
5.14 *

DUP050106736