

COOS - Insurance 1804 tinting white

CONSISTENCY Liquid

FOR USE ON

CUSTOMER

LABORATORY NO.

COST CLASS.

DATE 8/1/50

STRAINER

GRIND 2-3

MILL Pebble

WT. OR BE 15.5

| CODE<br>NUMBER                                    | ONE GALLON BATCH |      |           | LARGE BATCH |      |      | IS AGITATOR REQUIRED                                                                                          |                 |
|---------------------------------------------------|------------------|------|-----------|-------------|------|------|---------------------------------------------------------------------------------------------------------------|-----------------|
|                                                   | PINTS            | LBS. | OZS.      | GALS.       | LBS. | OZS. | VISC. F.B.                                                                                                    | TEMP.           |
| W-69                                              |                  | 2    | 14        |             | 230  |      | 85-90KU                                                                                                       |                 |
| W-35                                              |                  | 5    | 3         |             | 115  |      | VISC. RED.                                                                                                    | TEMP.           |
| W-1                                               |                  | 2    |           |             | 160  |      | VISCOSIMETER                                                                                                  | Stormer         |
| W-10                                              |                  |      | 12        |             | 60   |      | COLOR                                                                                                         | SHEEN           |
| W-11                                              |                  | 2    | 13        |             | 225  |      | NON VOL.                                                                                                      | FLASH PT.       |
|                                                   |                  |      |           |             |      |      | MATCH FOR                                                                                                     |                 |
| O-1                                               | 2 7/8            |      |           | 28 3/4      |      |      | REDUCER                                                                                                       |                 |
| O-5                                               | 1 1/4            |      |           | 12 1/2      |      |      | AMT. FOR BRUSHING F.B.                                                                                        |                 |
| O-286                                             | 3/4              |      |           | 7 1/2       |      |      | SPRAYING                                                                                                      | TUMBLING        |
| W-VR 49098                                        | 3/4              |      |           | 7 1/2       |      |      | DIPPING                                                                                                       | DRIP TIME       |
| OR O-315                                          |                  |      |           |             |      |      | BAKE                                                                                                          | TEMP.           |
| S-43                                              | 1 3/4            |      |           | 17 1/2      |      |      | AIR DRIES IN overnight                                                                                        |                 |
| D-15                                              | 5/8              |      |           | 6 1/4       |      |      | A. O. TO RECOAT IN 72 hours                                                                                   |                 |
| W-25                                              |                  |      | 2 loz/gal |             |      |      | REMARKS: Use this formula until W-170 can be obtained in sufficient quantity then new formula will be issued. |                 |
| * Add if needed to bring viscosity up to standard |                  |      |           |             |      |      |                                                                                                               |                 |
| ** Drisoy O-315 can be used to replace W 49098    |                  |      |           |             |      |      |                                                                                                               |                 |
| YIELD                                             | 1 gal            |      |           | 149 1/2 lbs |      |      | FORMULATOR                                                                                                    | 1 Wangsness 103 |
|                                                   |                  |      |           |             |      |      |                                                                                                               | 26-4-6          |

Standard Formula  
Not to be taken  
from File.

N12034

GLD058982

| COST | DATE | ANALYSIS                   | CUSTOMERS                 |
|------|------|----------------------------|---------------------------|
|      |      | PIGMENT 62.3 %             |                           |
|      |      | VEHICLE 37.7 %             |                           |
|      |      | 100.0%                     |                           |
|      |      | PIGMENT                    |                           |
|      |      | Lithopone 21.1%            |                           |
|      |      | Basic Lead Sulfate 14.7    |                           |
|      |      | 10% Leaded Zinc Oxide 38.1 |                           |
|      |      | Magnesium Silicate 20.6    |                           |
|      |      | Barium Sulfate 5.5         |                           |
|      |      | 100.0%                     | <i>All plants 9-27-50</i> |
|      |      | VEHICLE                    |                           |
|      |      | Linseed Oil 47.5%          |                           |
|      |      | Treated Soya Oil 26.0      |                           |
|      |      | Mineral Spirits 19.0       |                           |
|      |      | Liquid Drier 7.5           |                           |
|      |      | 100.0%                     |                           |

GLD058983