VISCOSITY WORK SHEET

Item	P.T.No.	Date 5/20/55
Worker H. Stanley	Polymer Lucite	Solvent EDC
For Graf	Charge 1290	Temperature 25°C
Viscometer No. I	Efflux Time 221.0	Weight: Gross 2.5988
Viscometer No. 2	Efflux Time 219.4	Tare 2.4738
Viscometer No.	Efflux Time	Net .1250

Sample	Flask	Visc. No.	Solution Efflux Times	Rel. Inh. visc. Visc. or M.W.	
14-257	21	I	272.6; 272.7; 272.5;	1.234	91500
"	H-2	2	270.7; 270.9; 270.8; 270;	1.236	98,500

PC-1

N38734