

CG 18CODE GC-1-A PKG.

→ OCT 29 00 37521

EST. WGT. 2166 LBS.

PROCESSING INSTRUCTIONS BATCH UNIT

PREPARED BY (C) GC-1-A	APPROVED BY AJC 1-10-78 DCG 1-13-78
TYPED BY NSA 3-14-78	
MAKING NOTES	

REMARKS

NAME: MONASTRAL® GREEN G

NON-BLEEDING

INSTRUCTIONS				-PRESSING-		RECORD				
AT	213			PRESSLOAD	1ST	2ND	3RD	4TH	5TH	
ATE	6-29-80			STARTED	12:44					
IME	10:00			CAKES USED	24					
RELEASED BY	MA			WATER ON	12:44					
WESS	31			HRS. WASHED	4					
O. OF CAKES	44			OHMS	5000					
RESS WITH	AGITATION			HRS. WASHED						
ASH TO -3000	OHMS 135-145°F water			OHMS						
EST AFTER 20	HOURS			HRS. WASHED						
OAD in metal drums at 360# net wgt.				OHMS						
NOTE: 1. Request making reheat SV to 178-182°F once per shift				CAKE CONDITION						
2. Air-blow presscake when 3000 ohms reached for 15 min at 40 PSI				NO. CARS LOADED						
				EXPLAIN LOSSES						

SAMPLES Thief sample per SOP

DELIVER TO CTI

SAMPLED BY

RELEASED BY

-DRYING-

DO NOT DRY	LUMP: - OK - WET - SALTS - CONTAMINATED
	ADDITIONAL DRYING HOURS REQUIRED
	NO. DRUMS
SAMPLES	NO. CARS PULLED
DELIVER TO	LUMP WGT.
	SAMPLED BY
	RELEASED BY

-GRINDING-

ILL	SCREEN	RPM	SCREEN	RPM
MAX. TEMP.	°F		MAX. TEMP.	°F
			EXPLAIN LOSSES	
SAMPLE AFTER / WITHOUT MIXING			DATE MIXED	
SAMPLES				
DELIVER TO	CTL		SAMPLED BY	RELEASED BY