

CO 03 CODE KY-787-D PKG.

JAN 12 33779

EST. WGT. 1921 ~~2232~~ LBS.

BASS
per Control Lab
1980

6980

TOTAL WGT 7230
6121# (REQ)

PROCESSES
KY-787-D (S)
Alternate
TYPED BY
JIC 11-4-77
MAKING NOTES

REMARKS

ME: KROLOR® YELLOW-MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

AT					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
TE			262		STARTED	330pm				
ME			1-14-80		CAKES USED	84				
RELEASED BY			1pm		WATER ON	9pm				
RESS	96	96	95		HRS. WASHED	4				
O. OF CAKES	70	72	84		OHMS	2500				
RESS WITH					HRS. WASHED					
ASH TO	2000				OHMS					
EST AFTER	4				HRS. WASHED					
OAD ON 10 CARS					OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	13				
					EXPLAIN LOSSES					

A.K.

SAMPLES 1-8 oz. JAR
ELIVER TO CTL FOR COLOR

SAMPLED BY

RELEASED BY

-DRYING-

DRY 12 HRS AT 2200F.
THEN DRY 8 HRS AT 1600F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
ELIVER TO

NO. CARS PULLED
SAMPLED BY

No. Drums: 31
LUMP WGT. 7107
RELEASED BY

-GRINDING-

ILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE A: WITHOUT MIXING
AMPLES 1 env + 1 Pt Can
ELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

N 261

33779
422
41

0.00 *

0.00 *

2.38 +
0.12 -
2.55 +
0.14 -
2.58 +
0.14 -
2.59 +
0.14 -
2.49 +
0.14 -
2.42 +
0.14 -
2.27 +
0.14 -
2.37 +
0.14 -
2.36 +
0.14 -
2.36 +
0.14 -
2.39 +
0.14 -
2.35 +
0.14 -
2.43 +
0.14 -
2.44 +
0.14 -
2.39 +
0.14 -
2.54 +
0.14 -
2.50 +
0.14 -
2.36 +
0.14 -
2.48 +
0.14 -
2.52 +
0.14 -
2.48 +
0.14 -
2.48 +
0.14 -
2.52 +
0.14 -
2.52 +
0.14 -
2.51 +
0.14 -
2.44 +
0.14 -
2.38 +
0.14 -
2.33 +
0.14 -