

RAW MATERIAL CHARACTERISTICS AND TESTING

Exp'tal No. _____ Sample Report _____ Card No. 2 Date 1/29/48 No. BW 102
 Name (Trade) Basic Carbonate White Lead Paste Replaces Card No. _____
 Name (Chemical) _____
 Material (Class) White Pigment
 Usage Exterior Paints Storage Loss _____
 Approximate Price _____ Date _____ % in Tanks _____
 Bulk 3.46 Gal./100 lbs.: Lb./Gal. 29.3 @ _____ °F. % in Drums _____

SIMILAR MATERIALS

BW 103 76% Pulp
 Rx 17 88% Soft Paste

ROUTINE TESTS (Must be Run on Each Shipment)

TEST	Min.	Stan.	Max.	Method
Water, %			1.0	408
Wt./Gal., lbs	28.0		30.0	401.0
Color vs 18 dry			421.2	421.2
			or	421.1


SECONDARY TESTS (Run Different One Each Shipment)

TEST	Min.	Stan.	Max.	Method
Total Residue on 325 Mesh, %			1.5	409
Pigment, %	84.0		86.0	402.1
Linseed Oil, %	13.5		15.5	*

*Subtract pigment plus water from total.

0007-SWP-0048394

N15805

SUPPLIER'S NAME	SUPPLIER'S CODE No.
National Lead Co.	BW 102 White Lead in Oil
Specification: Issued on 11-25-47 by V. L. Sahli Standard Sample Established Use 18 dry std. Assignment Requested by	
REMARKS: 	

0007-SWP-0048395

22 16 HV 91 NVP 86


RECEIVED
 APR 1 1948
 SHELL

RAW MATERIAL CHARACTERISTICS AND TESTING									
Exp'tal No. _____		Sample Report _____		Card No. <u>2</u>		Date <u>1/29/48</u> BW 103			
Name (Trade) <u>Basic White Lead Carbonate in Oil</u>						Replaces Card No. _____			
Name (Chemical) _____						SIMILAR MATERIALS			
Material (Class) <u>White Pigments</u>						BW 102 85% Pulp			
Usage <u>Exterior Paints</u>						Rx 17 88% Soft Paste			
Approximate Price _____ Date _____						% in Tanks _____			
Bulk <u>4.46</u> Gal/100 lbs.; Lb./Gal <u>22.4</u> @ _____ *F. _____						% in Drums _____			
ROUTINE TESTS (Must be Run on Each Shipment)					SECONDARY TESTS (Run Different One Each Shipment)				
TEST	Min.	Stan.	Max.	Method	TEST	Min.	Stan.	Max.	Method
Water, %			1.0	408	Total Residue on 325 Mesh, %			1.5	409
Wt./Gal., lbs @ 75 deg F.	22.0		23.0	401.0	Pigment, %	75.0		77.0	402.1
Color vs 18 dry				421.2 or 421.1	Linseed Oil, %	22.0		24.0	
					*Subtract pigment plus water from total.				

N15805.01

0007-SWP-0048396

SUPPLIER'S NAME	SUPPLIER'S CODE No.
National Lead Co.	EW 103 White Lead in Oil
Specification: Issued on 11-25-47 by V. L. Sahli	
Standard Sample Established Use 18 dry standard	
Assignment Requested by	
REMARKS:	



CHICAGO PAINT RESEARCH CO.
APR 1 1948
RECEIVED

10-46 5-1785

0007-SWP-0048397