CODE 710787 LOT 361062

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
2360	1	T-76		
2315	1	T-212		
	STUMP	Lumps 4,457		

TOTAL NET WT. 4,675 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
JT	6/25/10	

N32349

25
2447

CG 04 CODE KO-789-D PKG. _____

→ JUL 15 36182

EST. WGT. ~~1199~~ 1032 LBS.

OK
AP

Total Weight ~~5199#~~ 5232 5332 (Req. _____)

PROCESSING INSTRUCTIONS: BATCH

PROCESSES	APPRO/E
KO-789-D (I)	FWK 9
	UCG 9-
	MTW 10
TYPED BY	
JJc 10-8-76	

MAKING NOTES

REMARKS

NAME: "KROLOR" ORANGE Y NON-BLEEDING

EC

INSTRUCTIONS					-PRESSING- RECORD				
VAT	2447				PRESSLOAD	1ST	2ND	3RD	4TH
DATE	6-14-80				STARTED	2P			
TIME	2:30 PM				CAKES USED	46			
RELEASED BY	C. [illegible]				WATER ON	2:45			
PRESS	22	23	24	25	HRS. WASHED	11A			
NO. OF CAKES	46	46	52	48	OHMS	5000			
PRESS with AGITATION					HRS. WASHED				
WASH TO 5000 OHMS with 35-75°F water					OHMS				
TEST AFTER 6 HOURS					HRS. WASHED				
LOAD on 6 cars					OHMS				
					CAKE CONDITION				
					NO. CARS LOADED	8			
					EXPLAIN LOSSES	Possible color loss. Presscake very sloppy wet			
SAMPLES 1 - 8 oz. jar					SAMPLED BY		RELEASED BY		
DELIVER TO CTL for color									

-DRYING-


DRY 16 HOURS AT 220°F	LUMP: - OK - WET - SALTS - CONTAIN
	Color lost See above note
	ADDITIONAL DRYING HOURS REQUIRED
	NO. DRUMS 13
SAMPLES	NO. CARS PULLED LUMP WGT 4657
DELIVER TO	SAMPLED BY RELEASED BY

-GRINDING-

938 HSP 3/32" RP SCREEN 3500 RPM	SCREEN RPM
TEMP. 210 °F	MAX. TEMP. °F
	EXPLAIN LOSSES
SAMPLE WITHOUT MIXING	DATE MIXED
SAMPLES 1 Env. + 1 Pint Can	
DELIVER TO CTL	SAMPLED BY

N32349.01

DUP050457652



N32349.02

DUP050457653