MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY-788 LOT 34865

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
50	70	3500		
	STUMP			

TOTAL NET WT. 3,500 PKG. N–CODE 1130

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	3/21/80	

22

244 CC 03 CODE KY-788-D PKG. ____

→ MAR 18 34856

EST. WGT. 960 860 LBS. OK HP

Total Wgt 3560# 3460

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	KY-788-D (K)	EWK 9/22/76
	Alternate	DCG 9/27/76
	TYPED BY	
	NE 2/24/76	

MAKING NOTES

REMARKS

AME: "KROLOR" YELLOW - LIGHT NON-BLEEDING

INSTRUCTIONS -PRESSING- RECORD

						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
AT	244					STARTED	11:15AM				
ATE	3-19-80					CAKES USED	46				
IME	11:00 AM					WATER ON	2PM				
ELEASED BY	C.M.					HRS. WASHED	2 HRS				
RESS :	22	23	~~24~~	24	~~25~~	OHMS	2000				
O. OF CAKES	46	46	~~46~~	52	~~50~~	HRS. WASHED					
RESS with		AGITATION				OHMS					
ASH TO 2000		OHMS with 35-75°F water				HRS. WASHED					
EST AFTER 2		HOURS				OHMS					
OAD on 6 cars						CAKE CONDITION					
						NO. CARS LOADED	6				
						EXPLAIN LOSSES					

AMPLES 1- 8oz JAR

DELIVER TO CTL for color

SAMPLED BY [illegible] RELEASED BY [illegible]

-DRYING-

Dry 12 hrs at 220 °F

Then Dry 8 hrs at 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

m

No. Drums 14

AMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT. 3516

SAMPLED BY RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM	SCREEN RPM
MAX. TEMP. 150 °F	MAX. TEMP. °F
	EXPLAIN LOSSES
SAMPLE WITHOUT MIXING	DATE MIXED
SAMPLES Env & 1 Pt Can	
DELIVER TO CTL	SAMPLED BY RELEASED BY

DUP050094614



DUP050094615