CODE 217673 LOT 3706 9

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
	7	1189	16	
	STUMP	LAMP UNIT	1193	

TOTAL NET WT. 1189 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

10/21 292

D.T

170.+
179.+
207.+
210.+
206.+
173.+
38.+
1189.T

36

100 CG 36 CODE RT-695-D PKG. ____

SEP--9-80 37064

EST. WGT. 1350 LBS.

(7)

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
RT-695-D (M)	DCG 1-12
	THD 2-25
TYPED BY	
LG 5-15-72	

~~Retyped 2-27-80~~ MnM

MAKING NOTES

REMARKS

NAME: BON RED DARK NON-BLEEDING

INSTRUCTIONS — PRESSING — RECORD

						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
VAT	100					STARTED	2[illegible]				
DATE	9/10/80					CAKES USED	30				
TIME	1:45PM					WATER ON	9:15				
RELEASED BY	DJ					HRS. WASHED	12				
PRESS	32	33	35	38	39	OHMS	4200				
NO. OF CAKES	60	60	60 (36) 30	60	60	HRS. WASHED					
PRESS Without AGITATION						OHMS					
WASH TO 4000 OHMS with 35-75F water						HRS. WASHED					
TEST AFTER 16 HOURS						OHMS					
LOAD on 8 cars						CAKE CONDITION					
						NO. CARS LOADED	4				
						EXPLAIN LOSSES					

A.K.

SAMPLES

DELIVER TO

SAMPLED BY RELEASED BY

--DRYING--

HOURS Dry 24 hours at L.V. H.V.

TEMP. 180 °F °F

SE 15-30

Mn Color

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

No Record of any Processing Loss

SAMPLES

DELIVER TO

NO. CARS PULLED 4 LUMP WGT. 9193

SAMPLED BY RELEASED BY

--GRINDING--

MILL 5 HSP 1/8" RP SCREEN 4600 RPM

MAX. TEMP. °F

Mn Color

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE ~~AFTER~~ / WITHOUT MIXING

SAMPLES 1 Env & 2 pt cans

DELIVER TO CTL

DATE MIXED 10/1/80

SAMPLED BY RELEASED BY

DUP050107274

4.62 *

37064
51
119

0.00 *

2.44 +
0.14 -
2.60 +
0.14 -
2.30 +
0.14 -
2.36 +
0.14 -
2.52 +
0.14 -
0.55 +
0.14 -
11.93 *

DUP050107275