MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Ky. 788 LOT 34886

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
1710	1	T. 327		
1550	1	T. 233		
	STUMP			

TOTAL NET WT. 3260 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

3/16/80

DUP050094692

22

243 CG 03 CODE KY-788-D PKG. ____

→ MAR 14 34886

EST. WGT. 960 860 LBS.

OK

HP

3460

Total Wgt. 3560# Req(_____)

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-788-D (J)	EWK 9/22/76
	DCG 9/23/76
TYPED BY	
NE 2/17/77	

MAKING NOTES

REMARKS

NAME: "KROLOR" YELLOW - LIGHT NON-BLEEDING

INSTRUCTIONS

VAT	243				
DATE	3-14-80				
TIME	2:00PM				
RELEASED BY	C. M.				
PRESS	22	23	24		
NO. OF CAKES	46	46	46		

PRESS With AGITATION

WASH TO 2000 OHMS with 35-75°F water

TEST AFTER 2 HOURS

LOAD on 6 cars

SAMPLES 1- 8oz JAR

DELIVER TO CTL for Color

-PRESSING- RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	2PM				
CAKES USED	46				
WATER ON	5PM				
HRS. WASHED	3				
OHMS	2000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	6				

EXPLAIN LOSSES

SAMPLED BY LAB RELEASED BY JC

-DRYING-

Dry 12 hrs at 220 °F Dry

Then Dry 8 hrs at 160 °F

SAMPLES

DELIVER TO

LUMP: - OK - WET - SALTS - CONTAMINATED

No Record of any PROCESSING LOSS

ADDITIONAL DRYING HOURS REQUIRED

No Drums 14

NO. CARS PULLED LUMP WGT. 3309

SAMPLED BY RELEASED BY BLL

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 150 °F

SAMPLE AFTER / WITHOUT MIXING

SAMPLES 1 Env. & 1 Pt can

DELIVER TO CTL

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY RELEASED BY

DUP050094693

3488.86	#
41.00	#
.18	#
.00	T
2.48	
.14	-
2.55	
.14	-
2.60	
.14	-
2.55	
.14	-
2.52	
.14	-
2.57	
.14	-
2.54	
.14	-
2.57	
.14	-
2.41	
.14	-
2.46	
.14	-
2.40	
.14	-
2.42	
.14	-
2.51	
.14	-
2.42	
.14	-
33.04	T

DUP050094694