



Test Report

Report No. A2200090001101001

Page 1 of 4

Applicant CHANGZHOU XCF POLYMER MATERIALS CO., LTD.

Address NO.999 DINGJIAN ROAD, DINGYAN TOWN, CHANGZHOU, 213025 CHINA

The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client

Sample Name PTFE White Sewing Thread
Part No. 1200Denier
Sample Received Date Apr. 14, 2020
Testing Period Apr. 14, 2020 to Apr. 28, 2020

Test Conducted:

As requested by the applicant. For details refer to next page(s).



Tested by

Ben Zou

Reviewed by

Fiona Wu

Approved by

Hill Zheng

Hill Zheng

Technical Manager

Apr. 28, 2020

No. R187211363



Centre Testing International Group Co., Ltd.

Inspection & Testing Services

CTI Building, Xing Dong Community, Xin'an Sub-district, Bao'an District, Shenzhen City, Guangdong Province, P.R. China

Test Report

Report No. A2200090001101001

Page 2 of 4

Executive Summary:

TEST REQUEST

Refer to FDA 21CFR 177.1550 Perfluorocarbon resins

- Total extractives
- Fluoride extractives

CONCLUSION

PASS

PASS

PASS (FAIL) means that the results shown on the report (do not) comply with the required limits.

***** For further details, please refer to the following page(s) *****

Test Report

Report No. A2200090001101001

Page 3 of 4

Refer to FDA 21CFR 177.1550 Perfluorocarbon resins

▼ Total extractives

Test Method: Refer to FDA 21CFR 177.1550

Test Item(s)	Result	MDL	Reference Limit	Unit
	001			
Distilled water extractives	1.0	0.5	3.1	mg/dm ²
50% ethanol extractives	0.7	0.5	3.1	mg/dm ²
N-heptane extractives	1.7	0.5	3.1	mg/dm ²
Ethyl acetate extractives	2.1	0.5	3.1	mg/dm ²

▼ Fluoride extractives

Test Method: Refer to FDA 21CFR 177.1550

Test Item(s)	Result	MDL	Reference Limit	Unit
	001			
Fluoride extractives in distilled water	N.D.	0.05	0.46	mg/dm ²
Fluoride extractives in 50% ethanol	N.D.	0.05	0.46	mg/dm ²
Fluoride extractives in n-heptane	N.D.	0.05	0.46	mg/dm ²
Fluoride extractives in Ethyl Acetate	N.D.	0.05	0.46	mg/dm ²

Remark:

- MDL = Method Detection Limit
- N.D. = Not Detected (<MDL)

Sample/Part Description

001 White plastic thread

Note:


- The testing data and result(s) in this report is(are) just for scientific research, education, internal quality control and product development etc.

Test Report

Report No. A2200090001101001

Page 4 of 4

Photo(s) of the sample(s)



*** End of Report ***

Statement:

1. This report is considered invalid without approved signature, special seal and the seal on the perforation;
2. The sample(s) and sample information was/were provided by the client who should be responsible for the authenticity which CTI hasn't verified;
3. The result(s) shown in this report refer(s) only to the sample(s) tested;
4. Without written approval of CTI, this report can't be reproduced except in full;
5. In case of any discrepancy between the English version and Chinese version of the testing reports (if generated), the Chinese version shall prevail.

有限公司