

% mass loss						
Plasma Exposure Time	PTFE	Alternative 1	Alternative 2	Alternative 3	Alternative 4	Alternative 5
0h	0%	0%	0%	0%	0%	0%
2h	0%	2%	2%	1%	1%	2%
4h	0%	4%	4%	3%	3%	4%
6h	0%	6%	7%	5%	5%	6%
8h	0%	9%	10%	7%	7%	8%
10h	0%	11%	12%	9%	9%	9%
12h	0%	14%	15%	11%	11%	11%
14h	0%	16%	18%	12%	13%	13%
16h	0%	18%	22%	14%	15%	14%

