MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE 15y788 LOT 3438.0

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
50	73	3,650		
	STUMP			

TOTAL NET WT. 3,650 PKG. N–CODE 1130

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	2/21/80	

N 27572

25
2/62

GG 03 CODE KY-788-D PKG. ____

→ FEB 14 34380

EST. WGT. 960 LBS.

OK
AP

Total Wgt 3560#

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-788-D (K)	EWK 9/22/76
Alternate	DCG 9/27/76
TYPED BY	
NE 2/24/76	

MAKING NOTES

REMARKS

NAME: "KROLOR" YELLOW - LIGHT NON-BLEEDING

INSTRUCTIONS -PRESSING- RECORD

						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
VAT	2162					STARTED	6:22 PM				
DATE	2-16-80					CAKES USED	UD				
TIME	5:40 PM					WATER ON	9 AM				
RELEASED BY	TCH					HRS. WASHED	3				
PRESS	22	23	~~24~~	24	95	OHMS	7000				
NO. OF CAKES	46	46	~~45~~	52	48	HRS. WASHED					
PRESS with		AGITATION				OHMS					
WASH TO	2000	OHMS with 35-75°F water				HRS. WASHED					
TEST AFTER	2	HOURS				OHMS					
LOAD	on 6 cars					CAKE CONDITION					
	TDS					NO. CARS LOADED	7				
						EXPLAIN LOSSES					

SAMPLES 1- 8oz JAR
DELIVER TO CTL for color

SAMPLED BY #469 RELEASED BY JK

-DRYING-

Dry 12 hrs at 220 °F
Then Dry 8 hrs at 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

m

No. Drums 16

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

LUMP WGT. 3621
RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES Env & 1 Pt Can
DELIVER TO C.T.L

DATE MIXED

SAMPLED BY RELEASED BY

N 27572.01

DUP050094833

34380
41
16

0.00 *

2.35 +
0.12 -
2.42 +
0.12 -
2.52 +
0.12 -
2.52 +
0.12 -
2.54 +
0.12 -
2.50 +
0.12 -
2.36 +
0.12 -
2.47 +
0.12 -
2.54 +
0.12 -
2.50 +
0.12 -
2.59 +
0.12 -
2.47 +
0.12 -
2.44 +
0.12 -
2.44 +
0.12 -
2.47 +
0.12 -
1.00 +
0.12 -
36.21 *

DUP050094834