

PFAS additive consumption during battery life

ref. 1

LiB cell Cycle times	The amount of residue of additive a listed in ref. 4	(wt.%)
0	2,00	
50	0,17	
100	0,15	
200	0,04	
300	0,01	

