

GOODS Endurance #1804 Tinting White

LABORATORY NO.

CONCENTRATION Liquid

COST CLASS.

DATE 8/3/53

FOR USE ON

STRAINER

GRIND 2-3

CUSTOMER

MILL Pebble or WT. OR BE 14.7

CODE NUMBER	ONE GALLON BATCH			LARGE BATCH			IS AGITATOR REQUIRED H1-R
	PINTS	LBS.	OZS.	GALS.	LBS.	OZS.	
W-35		3	15		315		VISC. F.B. 104-145 ⁰ TEMP.
W-1		1	9		125		VISC. BOX 85-90 K ⁰ P.
W-170		1	8		120		VISCOSIMETER #4 F.C. & Stormer
W-10		1	8		120		COLOR White SHEEN 65
W-188		3	11		295		NON VOL. FLASH PT.
							MATCH FOR Y-1804
O-1	2-7/8			28-3/4			REDUCER S-43
O-5	1-1/4			12-1/2			AMT. FOR BRUSHING
O-286	3/4			7-1/2			SPRAYING TUBELING
O-398	3/4			7-1/2			DIPPING DRIP TIME
S-43	1-3/4			17-1/2			BAKE TEMP.
D-15	5/8			6-1/4			
S-14			1			80	AIR DRIES IN 24 hrs.
*O-325			1			80	A. D. TO RECOAT IN 72 hrs.
							REMARKS:
							Standard Formula. Not to be taken from File.
							FORMULATOR Southwick - H.H.
							27-6
YIELD	1.36	Gal.					

* Hold to adjust body.

Changed to use W-188 instead of W-11.

