

RAW MATERIAL CHARACTERISTICS AND TESTING

Experimental No. _____ Sample Report _____ Date 7-16-43 No. 1031
 Name (Trade) Scotch Laddie White Lead Card No. 1 Replaces Card No. _____

Name (Chemical) <u>Lead Carbonate</u>	SIMILAR MATERIALS	
Material (Class) <u>Pigment</u>	<u>18</u>	
Usage <u>Paint</u>		
Approximate Price _____ Date _____		
Bulk <u>1.75</u> Gal./100 lbs. Wt./Gal. <u>57.14</u> @ _____ °F.		

ROUTINE TESTS (Must be Run on Each Shipment)					SECONDARY TESTS (Run Different One Each Shipment)				
TEST	Min.	Stan.	Max.	Method	TEST	Min.	Stan.	Max.	Method
Color				421.2	Res 325M		0.15%	0.5%	410
				or	Lead Carbonate			67%	706
				421.1	Moisture		0.7%	1%	407.1
Strength				422.2	Oil Abs.		14		419.2
Texture					By				
INACTIVE									

VOID

N15822

0007-SWP-0048471

SUPPLIER'S NAME	SUPPLIER'S CODE No.
John R. MacGregor Lead Co.	Scotch Laddie White Lead

Specification: Issued on

Standard Sample Established

Assignment Requested by

REMARKS:

0007-SWP-0048472