

Experimental No.	CW 769	Sample Report	Date 10-23-44 No. 1612
Name (Trade)	Mustone White Lead	Card No.	Replaces Card No.

Name (Chemical)	SIMILAR MATERIALS
Material (Class)	18
Usage	1
Approximate Price	BW 102 Pulp
Bulk 1.77 Gal. / 100 lbs. Wt. / Gal. 56.64 @	1031

ROUTINE TESTS (Must be Run on Each Shipment)					SECONDARY TESTS (Run Different One Each Shipment)				
TEST	Min.	Stan.	Max.	Method	TEST	Min.	Stan.	Max.	Method
Color				421.2	Res 325			0.1%	410
			or	421.1	PbCO ₃			68.6%	706
Strength				422.2	Pb(OH) ₂			30.95%	706
Texture					Lead Acetate			0.15%	717.0
					Moisture			0.30%	407.1
					Total Lead	80%		90%	704
									706
					Oil Abs.		9		419.2

N16341

SUPPLIER'S NAME	SUPPLIER'S CODE No.
	Euston Std White Lead

Specification : Issued on

Standard Sample Established

Assignment Requested by

REMARKS:

X167 5-45 3820

0007-SWP-063031