

MO-S-A
PACKAGE TICKET
 (DRY AND PASTE ONLY)

CODE Ky 787 LOT 38330

NET WT/PKG	NO. PKG	PACK. WT	LOCATION	PG
<u>2000</u>	<u>1</u>	<u>T-140</u>		
<u>1988</u>	<u>1</u>	<u>T-246</u>		
<u>2030</u>	<u>1</u>	<u>T-274</u>		

Label 6051

TOTAL NET WT 6018 PKG. N-CODE _____

PROD. SPVL _____ DATE 1-16-80 WHSE. OPER. _____

N34745

95
267

CG 03 CODE KY-787-D PKG.

→ DEC 19 80 38330

EST. WGT. 1921 LBS.

OK
18

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
KY-787-D (S)

APPROVED BY
EWK 10-19-77

Alternate

DCG 10-25-77

TYPED BY
JIC 11-4-77

MAKING NOTES

REMARKS

TOTAL WGT 5845# (REQ)

NAME: KROLOR® YELLOW-MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	262					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	12-22-80					STARTED	7:30				
TIME	10:10 PM					CAKES USED	22				
RELEASED BY	S.B.					WATER ON	6:00				
PRESS	98	96	95			HRS. WASHED					
NO. OF CAKES	78	72	72			OHMS					
PRESS WITH						HRS. WASHED					
WASH TO	2000					OHMS					
TEST AFTER	4					HRS. WASHED					
LOAD ON 10 CARS						OHMS					
						CAKE CONDITION	110				
						NO. CARS LOADED					
						EXPLAIN LOSSES					

SLV

SAMPLES 1-8 oz. JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY

RELEASED BY

SLV

-DRYING-

DRY 12 HRS AT 220°F.
THEN DRY 8 HRS AT 160°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

No. Drums: 26
LUMP WGT. 6051
RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 env + 1 Pt Can
DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

38330
41
197

2.46
0.12
2.45
0.12
2.52
0.12
2.70
0.12
2.70
0.12
2.51
0.12
2.50
0.12
2.40
0.12
2.55
0.12
2.42
0.12
2.44
0.12 -
26.33 *

38330
41
197

2.44 +
0.12 -
2.50 +
0.12 -
2.55 +
0.12 -
2.51 +
0.12 -
2.50 +
0.12 -
2.51 +
0.12 -
2.50 +
0.12 -
2.47 +
0.12 -
1.93 +
0.12 -
20.83 *

47.16 +
2.41 +
0.12 -
2.27 +
0.12 -
2.38 +

0.12 -
2.48 +
0.12 -
2.45 +
0.12 -
2.08 +
0.12 -
60.51 *

26.33 +
20.83 +
47.16 *

24
25
58
65