VISCOSITY WORK SHEET

Item 4698	P.T. No.	Date 4 | 3 | 56
Worker Stanley	Polymer Lucite	Solvent Chloroform
For Judge - Ex.	Charge 1840	Temperature 20°C.
Viscometer No. III	Efflux Time 159.7; 159.9	Weight: Gross 3.6058
Viscometer No. 8	Efflux Time 159.4; 159.4	Tare 3.4808
Viscometer No. A	Efflux Time	Net 0.1850

Sample	Flask	Visc. No.	Solution Efflux Times	Rel. Visc.	Inh. Visc. or M.W.
5202-08	13	III	213.2; 213.2	1.402	0.68
"	M39	8	221.9; 222.0; 221.9	1.398	0.66

PC-1

4/5/56 Lucas

N38920