

92/245
CODE YE-698-D PKG
LOT MAY -0.81- 1449

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

PROCESSES APPROVED BY
YE-698-D (S) F. POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS

= PRESSING =

RECORD

VAT
DATE
TIME
RELEASED BY
PRESS 2 92
NO. OF Cakes 54 54
PRESS WITH AGITATION
WASH TO 2000 OHMS WITH 35-75 F WATER
TEST AFTER 2 HOURS
LOAD ON 7 CARS

PRESSLOAD
STARTED
CAKES USED
WATER ON
HRS. WASHED
OHMS
HRS. WASHED
OHMS
HRS. WASHED
OHMS
CAKE CONDITION
NO CARS LOADED
EXPLAIN LOSSES

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT 5671

= GRINDING =

MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
SET ROOF BLAST GATE AT '9" FOR
HIGH AIR FLOW

RPM SCREEN
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

0.00 *

3.15	+
0.12	✓
3.42	+
0.12	✓
3.39	+
0.12	✓
3.65	+
0.12	✓
3.45	+
0.12	✓
3.42	+
0.12	✓
3.18	+
0.12	✓
3.29	+
0.12	✓
3.31	+
0.12	✓
3.36	+
0.12	✓
3.38	+
0.12	✓
3.45	+
0.12	✓
3.47	+
0.12	✓
3.41	+
0.12	✓
3.44	+
0.12	✓
3.11	+
0.12	✓
3.44	+
0.12	✓
1.55	+
0.12	✓
56.71	*