MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE [illegible] LOT [illegible]

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
	1	2244	T-190	
	1	2092	T-250	
	STUMP			

TOTAL NET WT. 4336 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

PH.

N32439

DUP050461235

7/240

CO 03 CODE KY-795-D PKG. ____

→ 35660

EST. WGT. ~~1178~~ 880 LBS.

OK / KP

4380

Total Wgt: ~~4878#~~ ~~4612#~~

PROCESSING INSTRUCTIONS: ~~BATCH~~ UNIT

PROCESSES	APPROVED BY
KY-795-D (I)	EWK 10/6/76
Alternate	DCG 10/7/76
TYPED BY	
NE 3/3/77	

MAKING NOTES

REMARKS

AME: "KROLOR" YELLOW-MEDIUM

NON-BLEEDING

-PRESSING-

INSTRUCTIONS					
AT	240				
ATE	5/8/80				
IME	7:10 pm				
ELEASED BY	S.B				
RESS	22	23	24	24	
IO. OF CAKES	46	46	46	52	

RESS with AGITATION

ASH TO 5000 OHMS

EST AFTER 5 HOURS with 35-75°F water

OAD on 5 cars

TDS

SAMPLES 1-8 oz JAR

DELIVER TO ctl for color

RECORD					
PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	1 pm				
CAKES USED	52				
WATER ON	5P				
HRS. WASHED	5				
OHMS	5000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	4				

EXPLAIN LOSSES

SAMPLED BY 1/32 RELEASED BY

-DRYING-

Dry 16 Hrs. at 220°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

No Drums : 15

SAMPLES

DELIVER TO

NO. CARS PULLED

LUMP WGT. 4446

SAMPLED BY

RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 210 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 Env & 1 Pt Can

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

N32439.01

DUP050461236

356.60N
41.00N
.18N
.00T

3.29
.14
3.08
.14
3.42
.14
3.27
.14
3.15
.14
3.30
.14
3.34
.14
3.21
.14
3.17
.14
3.50
.14
3.23
.14
3.21
.14
3.23
.14
3.35
.14
.81
.14
444.6T

N32439.02

DUP050461237