CG 03 CODE KY-908-D PKG ____

LOT L2J17 NOV 3 1982

EST. WT. 4226* LBS 240

(1)

PROCESSES: KY-908-D (G)

APPROVED BY FWP 06/30/82

MAKING NOTES _____

JOB NAME: 03KY908DPG

EC

= PRESSING =

INSTRUCTIONS				
VAT			240	
DATE			11-5-82	
TIME			5:15-4	
RELEASED BY			BR	
PRESS	2	22	23	24
NO.OF CAKES	46	46	46	52

PRESS WITH AGITATION

WASH TO 500 M MHOS - 135-145 F WATER

TEST AFTER 2 HOURS

LOAD ON 7 CARS

SAMPLES

DELIVER TO

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	7:30 am				
CAKES USED	46				
WATER ON	4:15 pm				
HRS. WASHED					
M MHOS	420				
HRS. WASHED	5				
M MHOS					
HRS. WASHED					
M MHOS					
CAKE CONDITION					
NO.CARS LOADED	4+3				

EXPLAIN LOSSES _____

SAMPLED BY

RELEASED BY SJL

= DRYING =

DRY 24 HOURS AT 180 F

NOTE: DRY ON FIRST STAGE ONLY.

RE-SET ON FIRST STAGE TIL DRY.

SAMPLES

DELIVER TO

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

NO CARS PULLED

SAMPLED BY

RELEASED BY

NO DRUMS 14

LUMP WGT ~~4216~~ 4213

2DP

= GRINDING =

MIL 939 HSR 3/32"RP SCREEN 3500 RPM

MAX. TEMP. 170 F

SAMPLE W/O MIXING 1 ENV & 2 PT CANS

IF PACKED IN BAGS SAMPLE AS FOLLOWS:

FIRST BAG 1 ENV.

40TH BAG 1 ENV. & 2 PINT CANS

LAST BAG 1 ENV.

DELIVER TO OIL

SCREEN RPM

MAX. TEMP. F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY

RELEASED BY

	0.00	*	
17			17
41			41
225			16
	0.00	*	0.00 *
			26.85 +
	3.15	+	3.82 +
	0.12	-/	0.12 -/
	3.02	+	3.34 +
	0.12	-/	0.12 -/
	3.19	+	3.70 +
	0.12	-/	0.12 -/
	3.17	+	3.20 +
	0.12	-/	0.12 -/
	3.05	+	1.82 +
	0.12	-/	0.12 -/
	3.05	+	42.13 *
	0.12	-/	
	3.23	+	
	0.12	-/	
	3.17	+	
	0.12	-/	
	2.90	+	
	0.12	-/	
	26.85	*	

DUP050059860