
FACT FINDER



PYDRAUL


AIR COMPRESSOR LUBRICANTS BY Monsanto

05L0469

TOWOLDMON0035656
WATER_PCB-00020125

Contents

PAGE	
1	The Pydraul Air Compressor Fact Finder
1	How Compressor Fires and Explosions Occur
3	Pydraul Fire-Resistance
4	Pydraul AC-A Virtually Eliminates Valve Deposits
5	Converting To Pydraul Is Easy
6	Pydraul Provides Excellent Lubricating Qualities
7	Mixing Compatability
7	Pydraul Is Used As A Lubricant For Compressors Made By All Major Manufacturers
8	Safe Handling



0510470

TOWOLDMON0035657
WATER_PCB-00020126

The Pydraul Air Compressor Fact Finder

. . . is designed to make the many facts about Pydraul® fire resistant lubricants for air compressors—Pydraul AC-A, Pydraul AC-A Winter Grade 28 and Pydraul 525A—easy to find.

These safety lubricants for air compressors were specially developed to offer you:

Safety from Fire and Explosion
Pydraul eliminates combustible mists and minimizes carbonaceous residues — greatly reducing the threat of compressor fires and explosions.

Lower Maintenance Costs
Pydraul eliminates deposits on exhaust valves, in coolers and in piping. You save the costs of compressor downtime and cleaning. Many compressor users find these savings alone justify using Pydraul lubricants.

How Compressor Fires & Explosions Occur

Every theory about the mechanisms of compressor fires and explosions hold one idea in common: petroleum oils are directly involved.

Petroleum Oil Mists & Films
Mist and accumulated films from petroleum oil in compressor systems can, under a variety of conditions, break down into combustible gases and carbonaceous residues that can ignite and produce an explosion, a receiver fire—or both. The U. S. Bureau of Mines[1] found that carbon deposits in air compressors lubricated with petroleum oil form a "carbon-oxygen complex." Oxidation forms this complex, and accelerated by heat, this oxidation process can lead to an explosion.

The Shortcomings of Safety Devices
Safety devices do not completely eliminate fire and explosion possibilities. A study on "The Mechanism of Explosions In Starting Air Lines,"[2] based on an exhaustive survey of compressor operations at 53 companies, reports that a stuck or leaking air check valve permits the engine being started to pack the section of line between the check and air timing valve with an explosive "oil residue-air" mixture. A pressure wave will force this mixture upstream into the main air line—and coupling this with good flame propagation in the power cylinder, the condition is laid for explosion in the pipe system.

Air line explosions and fires may even occur without the engine being started or before the ignition is turned on. Carbon and rust particles in a "hot" air line, due to operating an overheated compressor too long—hardly an improbable condition—can become saturated with oil, and with the flow of starting air, can cause these oil-saturated particles to flame.

Explosion Tests at 1300 PSI
The Walter Kidde Company, makers of fire extinguishing equipment, warns in a study[3] that users of high pressure air should guard against introducing a shock wave into high pressure lines by suddenly opening a plug cock in air compressor systems using petroleum oil. This report showed that in a 1-inch diameter tube, the inside walls filmed with oil, a sudden admission of air at pressures above 1300 psi caused combustion.

How can you eliminate the conditions that cause fires and explosions in air compressors? Eliminate the source of carbon deposits, the basic cause of most air compressor disasters—petroleum oil.

Substitute fire- and explosion-resistant Pydraul.

1. "The Carbon-Oxygen Complex as a Possible Initiator of Explosions and Formation of Carbon Monoxide in Compressed Air Systems," by Busch, Berger, and Schrenk, Bureau of Mines paper R.I.4465, June 1949.
2. "The Mechanism of Explosions in Starting Air Lines," by Ridgway, Robert S., *Petroleum Refiner*, June 1958.
3. "Oil Combustion Phenomena in High Pressure Air Systems," M. W. Weibel, Walter Kidde & Co., Inc., Report R-831, copyright 1952.

0510471

TOWOLDMON0035658
WATER_PCB-00020127

TABLE 1

	PYDRAUL AC-A	PYDRAUL AC-A WINTER GRADE 28
	Clear Blue Liquid	Clear Blue Liquid
	1.265—1.325	1.235—1.255
	0.35	0.15
	0.15%	0.15%
	85 to 95 3.9 to 5.3 417.0 SSU 46.2 SSU 545 SSU 60 SSU	26 to 30 3.8 to 4.2 132.8 SSU 39.3 SSU 165 SSU 45 SSU
	-5°F.	—25°F.
	2.60	2.63
	350°F.	350°F.
	787°F.	810°F.
	0.00045	0.00041
	0.31	0.33
	0.068	0.068
	400,000	380,000
	46.0	41.0
	Negligible	Negligible

COMPATIBILITY WITH METALS


Pydraul air compressor lubricants are compatible with all construction metals including aluminum. In most operations, aluminum bearing surfaces will wear as long as any other metal surfaces lubricated with Pydraul if they have been anodized.

TABLE 2—VAPOR PRESSURE

Temperature		Vapor Pressure mm Hg		
°C.	°F.	PYDRAUL AC-A	PYDRAUL 625A	PYDRAUL AC-A WINTER GRADE 28
0	32	3.5×10^{-6}	0.30×10^{-6}	5.5×10^{-6}
10	50	11.0×10^{-6}	1.1×10^{-6}	17.5×10^{-6}
20	68	3.3×10^{-5}	4.0×10^{-6}	50×10^{-6}
40	104	2.4×10^{-4}	3.8×10^{-5}	3.5×10^{-4}
60	140	11.5×10^{-4}	2.3×10^{-4}	1.6×10^{-3}
80	176	5.0×10^{-3}	1.2×10^{-3}	6.6×10^{-3}
100	212	1.7×10^{-2}	0.55×10^{-2}	2.2×10^{-2}
150	302	0.26	0.13	0.31
200	392	2.2	1.4	2.3


Vapor Density=11.2 compared to value for air of one (1).

FIGURE 1—TYPICAL VISCOSITIES



0510472

TOWOLDMON0035659
WATER_PCB-00020128



Pydraul Fire-Resistance


Pydraul fire-resistant fluids and lubricants have worked in industry since 1951, providing many millions of machine hours of fire-free operation. Never during these hours of machine operation has a Pydraul fluid contributed to a fire—and never since their introduction in 1954 has any Pydraul fire-resistant compressor lubricant caused a compressor fire or explosion.

FIRE-RESISTANCE TESTS OF PYDRAUL AC-A, PYDRAUL AC-A WINTER GRADE AND PYDRAUL 625A


TEST	RESULTS
High Pressure Spray Test AMS-3150C and Federal Test Method Std. 791. Test fluid sprayed at 1000 psi through orifice, passing through flame of oxyacetylene torch, 6000°F.	Does not flash or ignite up to 3½ feet from orifice.
Atomized Spray Test (procedure used by Factory Mutual Engineering Division). Test fluid heated to 140°F. sprayed at 1000 psi from atomized cone type nozzle. A torch is passed through this spray 2 feet and 2 to 6 inches from the orifice.	Local burning by torch at 6 inches and 2 feet from orifice. Flames self-extinguishe immediately when torch removed.
Hot Manifold Test (Federal Test Method Std. 791). Test fluid dripped on tube at 1300°F.	Does not flash or burn.
Molten Metal Ignition Test. Test fluid exposed to the surface of aluminum alloy at 1200°F., to test for spontaneous ignition.	Does not ignite.

0510473

TOWOLDMON0035660
WATER_PCB-00020129



500 hours on premium petroleum oil



500 hours on Pydraul AC-A

Pydraul AC-A Virtually Eliminates Valve Deposits

Compressor Data: 142 CFM, 6" LP Bore, 5" HP Bore, 5" Stroke, 870 RPM, 100 psi air

The photos compare exhaust valve deposits formed during individual 500-hour operations on two lubricants: a premium grade petroleum oil . . . and Pydraul AC-A*.

A glance at the photo of the valve lubricated with petroleum oil shows considerable carbon deposit build-up after 500 hours operation. The improvement in the valve condition in the photo on the right is obvious—virtually no carbon deposits after 500 hours operation with Pydraul AC-A. In the particular case, the compressor operator expects to get 7500 to 10,000 hours of service from Pydraul AC-A without shutting down—a 15- to 20-fold increase in operating time without a shutdown. Result: substantial maintenance savings in time and money—and virtual elimination of the fuel source of most air compressor fires and explosions.

*No photographs available of Pydraul 625A and Pydraul AC-A Winter Grade 28, but results are at least identical.

0510474

TOWOLDMON0035661
WATER_PCB-00020130

Converting To Pydraul Is Easy

First, simply drain the petroleum oil and wipe the crankcase or lubricator.

Thoroughly clean the exhaust valves and interstage equipment before filling the crankcase or lubricator with Pydraul. Pydraul will loosen carbonaceous deposits, varnishes and sludge. Unless these loosened deposits are cleaned from the system, they could clog pipelines and components, requiring additional downtime and production loss. Once the valves have been thoroughly cleaned of potentially dangerous carbon deposits, Pydraul lubricants will keep them clean—and let compressors run longer between maintenance shutdowns.

STANDARD CHECK FOR COMPRESSORS—Plastic separator bowls.
Not all plastic separator bowls are suitable for Pydraul service. Certain plastics are "crazed" or softened when exposed to Pydraul. Bowls made of glass, brass, steel, and these plastics—polycarbonate, polyethylene, or nylon—are recommended for use with Pydraul. If you have a question regarding the resistance of a particular plastic, Monsanto will be happy to advise you.

Diaphragm valves. Pydraul lubricants have a softening effect on neoprene and buna N rubber diaphragms normally used for petroleum oil service. These diaphragms should be replaced with butyl rubber, EPR (ethylene propylene rubber), fluoroelastomer, silicone or other compatible elastomer materials resistant to Pydraul fluids. Diaphragm sheeting is available from normal sources of supply.

All diaphragms in unloading valves or downstream control valves should be replaced at the time of changeover. Diaphragms in valving downstream from separator systems or drying systems need not be replaced at changeover time, but should be changed on a preventative maintenance schedule as soon as practicable after operation on Pydraul is begun.

For air compressors supplying air for instrumentation functions, mist eliminator systems are recommended to remove lubricant mists and moisture from air streams. A Monsanto development, a Brink® mist eliminator is a particularly effective system, available from Monsanto in a series of low-cost mist eliminator systems to operate at all capacities. For information on a Brink series suitable for your compressor system, write to:

Monsanto Enviro-Chem Systems, Inc.
800 North Lindbergh Blvd.
St. Louis, Mo. 63166
Telephone: (314) 694-2286
(Joseph A. Brink)

SPECIAL CHECK FOR SPLASH-LUBRICATED COMPRESSORS

Crankcase paint. Pydraul air compressor lubricants will soften and loosen some paints from crankcase interiors. These paint particles could block the lubricant passages. For this reason, it is a good practice to remove paint from crankcase interiors *before* Pydraul is added to the system. Standard paint removers are adequate for removing this paint.

SPECIAL CHECK FOR FORCE-FEED LUBRICATORS

Sight-glass fluid. If a separate force-feed lubricator of the type normally filled with water and glycerine is used, one of two changes is necessary: either replace the sight-glass fluid with one heavier than Pydraul or insert a metal bobber in the sight-glass. Pydraul fluids are heavier than water or glycerine and will not rise through these standard sight-glass liquids. Fluorochemical 101, a clear liquid supplied by the Minnesota Mining and Manufacturing Company, has a higher density than Pydraul and is a completely satisfactory replacement.

Metal bobbers. The alternate to using Fluorochemical 101 is to modify the sight-glass lubricator by inserting a simple metal bobber. The bobber is installed by draining the sight-glass liquid, removing the guide wire and inserting the bobber. Operation of the lubricator is then indicated by movement of the bobber with each stroke of the pump plunger instead of counting the drops as with guide wires. Bobbers are available for either McCord, Manzell, or Lincoln Engineering lubricators. Modification of the Madison-Kipp lubricator requires replacement of the entire sight-glass.

Vacuum-sight lubricators. Vacuum-sight lubricators require no modification for Pydraul usage.

0510475

TOWOLDMON0035662
WATER_PCB-00020131

Pydraul Provides Excellent Lubricating Qualities

TABLE 3
FALEX LOAD TEST

	PASSING LOAD
Pydraul 625A	4250
Pydraul AC-A	4025
Pydraul AC-A Winter Grade 28	4175

TABLE 4
FALEX WEAR TEST

	WT. LOSS, PIN (mg.)	WT. LOSS, BLOCKS (mg.)
Pydraul 625A	1.1	5.8
Pydraul AC-A	0	0.5
Pydraul AC-A Winter Grade 28	0.6	0.9

TABLE 5
TIMKEN

	OK LOAD (lbs.)	FILM STRENGTH (psi)
Pydraul 625A	30	11,700
Pydraul AC-A	45	15,100
Pydraul AC-A Winter Grade 28	24	8,600

TABLE 6
SHELL FOUR-BALL WEAR

(167°F., 1 hour, 630 rpm., mm scar diameter)

STEEL ON STEEL	PYDRAUL 625A	PYDRAUL AC-A	PYDRAUL AC-A WINTER GRADE 28
10 kg	0.23	0.33	0.42
40 kg	0.60	0.67	0.66
STEEL ON BRONZE			
10 kg	0.46	0.48	0.43


DROP SIZE

Drop size of a lubricant is important to determine an adequate lubricant injection rate to insure proper compressor lubrication. The rate of lubrication is controlled by noting the drops per unit of time.

The drop size for the fluids tabulated below were determined by noting the number of drops formed at room temperature (75°F.) on a 1 mm I.D. by 3½ mm O.D. glass tip. (Larger or smaller drops will result if different sized tips are used.)

Fluid	Drops per cubic centimeter
Medium weight petroleum oil	33
Pydraul AC-A	39

When installing new equipment, *it is best to start with an increased lubricant feed rate and reduce this rate by successive increments. Inspection of cylinder walls and valves will indicate the proper degree of wetting.*



0510476

TOWOLDMON0035663
WATER_PCB-00020132


Mixing Compatibility


Pydraul AC-A, Pydraul AC-A Winter Grade 28 and Pydraul 625A are completely miscible in all proportions with competitive synthetic phosphate ester lubricants.


Pydraul Is Used As A Lubricant For Air Compressors Made By All Major Manufacturers


New air compressors of most types and sizes produced by major compressor manufacturers can be manufactured for lubrication with Pydraul. The manufacturers listed (below) have manufactured compressors equipped for Pydraul, upon specification of the buyer, for over ten years. Many compressors have operated on Pydraul lubricants continually with exhaust air temperatures of 350°F. Pydraul is also used to lubricate cylinders in compressors operating at pressures over 4500 psig.

American Messer Corporation
Atlas Copco
Bury Compressor Company
Carrier Corporation
Chicago Pneumatic Tool Company
Clark Brothers Company, division of Dresser Industries
Cooper-Bessemer Corporation
DeLaval Steam Turbine Company
Gardner-Denver Company
Ingersoll-Rand Company
Joy Manufacturing Company
Kinney Manufacturing, division of The New York Air Brake Company
Norwalk Company, Incorporated
Schramm, Incorporated
Worthington Corporation









0510477

TOWOLDMON0035664
WATER_PCB-00020133

Safe Handling

There has been no reported case in many years of service to indicate any special health hazard with Pydraul air compressor lubricants. However, as with all specialized industrial fluids and lubricants, certain precautions are advisable.

Animal toxicity screening studies indicate Pydraul AC-A, Pydraul AC-A Winter Grade 28 and Pydraul 625A may be considered only slightly toxic from the standpoint of accidental ingestion or skin absorption. It does not appear to have any significant potential for skin or eye irritation. Because these fluids have excellent solvent properties, repeated or prolonged skin contact could lead to defatting and drying of the skin; thus reasonable personal hygiene practices are recommended to avoid prolonged and repeated skin exposure.

If Pydraul fluids are splashed or sprayed into the eyes, moderately severe pain and irritation may result. There is no evidence to show Pydraul causes permanent eye tissue damage. Eyes should be thoroughly flushed with water and the workman referred to a physician. To relieve irritation, physicians have used 1% pontocaine solution, as well as the ophthalmic cortisone acetate solution.

Vapor inhalation. At room temperatures, there is no vapor inhalation hazard from Pydraul fluids. Although there has been no problem with high concentration of vapors, inhalation of vapors at high temperatures should be prevented.

If the compressed air is to be used for air line masks, respirators and other inhalation equipment, it is always recommended that a commercial filter cartridge for air-supplied masks be incorporated in the compressor air line to remove any foreign matter. This is good industrial practice for any compressor fluid or lubricant.

0510478

TOWOLDMON0035665
WATER_PCB-00020134

DISTRICT SALES OFFICES ALL DIVISIONS

AKRON, OHIO 44313
260 Springside Drive
Montrose Development Park
Tel. (216) 666-4111

ATLANTA, GEORGIA 30326
Lenox Towers East
3400 Peachtree Rd. N. E. — Suite 1711
Tel. (404) 577-2260

BOSTON, MASSACHUSETTS 02149
Everett Station
Tel. (617) 387-5010

CHICAGO, ILLINOIS
3158 Des Plaines Ave.
Des Plaines, Illinois 60018
Tel. (312) 296-6688

CINCINNATI, OHIO 45206
1501 Madison Road
Tel. (513) 751-6707

DETROIT, MICHIGAN 48235
500 Northland Towers East
Tel. (313) 357-0910

HONOLULU, HAWAII 96812
205 Pacific International Bldg.
677 Ala Moana Blvd., P. O. Box 3824
Tel. (808) 531-2744

HOUSTON, TEXAS 77027
1301 Post Oak Tower
5051 Westheimer Road
Tel. (713) 621-9550

LOS ANGELES, CALIFORNIA 90022
6670 E. Flotilla St.
Tel. (213) 723-2492

NEW ENGLAND AREA
Hydrocarbons & Polymers Div.
730 Worcester St., Indian Orchard, Mass. 01051
Tel. (413) 788-6911
Plastic Products & Resins Div.
P. O. Box 2130, Springfield, Mass. 01101
Tel. (413) 788-6911

NEW YORK, NEW YORK 10017
277 Park Avenue
Tel. (212) 922-4111

ST. LOUIS, MISSOURI 63166
800 N. Lindbergh Blvd.
Tel. (314) 694-1000

SAN FRANCISCO BAY AREA
2710 Lafayette, Santa Clara, Calif. 95052
Tel. (408) 243-0414

SEATTLE, WASHINGTON 98121
2112 Third Avenue
Tel. (206) 622-4203

WILMINGTON, DELAWARE 19803
2005 Concord Pike, Fairfax
Tel. (302) 658-6531

Additional District Offices are maintained by:

Agricultural Division

ALLENTOWN, PENNSYLVANIA 18104
Park Professional Building
2200 Hamilton Street
Tel. (215) 437-5471

DECATUR, ILLINOIS 62523
207 Decatur Professional Building
363 South Main Street
Tel. (217) 423-6031

DES MOINES, IOWA 50310
312 Merle Hay Tower
Tel. (515) 276-8503

FREMONT, NEBRASKA 68025
150 South Main Street
Tel. (402) 727-1230

INDIANAPOLIS, INDIANA 46205
Suite 218, 4000 Meadows Drive Building
Tel. (317) 547-9148

KANSAS CITY, MISSOURI 64133
701 Blue Ridge Tower
4240 Blue Ridge Boulevard
Tel. (816) 353-8060

LULING, LOUISIANA 70070
P. O. Box 174
Tel. (504) 784-6263

MANKATO, MINNESOTA 56001
111 Madison East
Tel. (507) 387-3406

MEMPHIS, TENNESSEE 38104
303 Union Plaza Building
1835 Union Avenue
Tel. (901) 278-7811

MUSCATINE, IOWA 52761
P. O. Box 473
Tel. (319) 263-1331

Hydrocarbons & Polymers Division-Lion Oil

EL DORADO, ARKANSAS 71730
Lion Oil Building
Tel. (501) 863-3111

JACKSON, MISSISSIPPI 39209
P. O. Box 10937, Westland Station
Tel. (601) 352-3648

N. LITTLE ROCK, ARKANSAS 72119
410 West 8th Street, P. O. Box 5821
Tel. (501) 376-2437

MEMPHIS, TENNESSEE 38113
1023 Riverside Drive, P. O. Box 13248
Tel. (901) 948-4451

Organic Division *(Rubber Instruments)*

AKRON, OHIO 44311
920 Brown Street, P. O. Box 2307
Tel. (216) 434-1962

Plastic Products & Resins Division

EUGENE, OREGON 97401
P. O. Box 1819
855 Seneca Road
Tel. (503) 342-7201

KENILWORTH, NEW JERSEY 07033
North Seventh St. & Monroe Ave.
Tel. (201) 276-2900

Textiles Division

ATLANTA, GEORGIA 30303
Atlanta Merchandise Mart
240 Peachtree St., N. W.
Tel. (404) 577-2260

CHARLOTTE, NORTH CAROLINA 28210
6230 Fairview Road, Suite 400
Tel. (704) 364-0110

GREENVILLE, SOUTH CAROLINA 29606
McAlister Plaza
P. O. Box 5564, Station B
Tel. (803) 239-9171

NEW YORK, NEW YORK 10001
350 Fifth Ave.
Tel (212) 556-5100

0510479

TOWOLDMON0035666
WATER_PCB-00020135

"Nothing contained herein is to be construed as a recommendation to use any product in conflict with any patent. MONSANTO MAKES NO WARRANTIES AS TO THE FITNESS OR MERCHANTABILITY OF ANY PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations, and disclaims all liability for any resulting loss or damage."

0510460

Monsanto

Monsanto Company / Functional Fluids / 800 North Lindbergh Blvd. / St. Louis, Missouri 63166

0770-161-LRA Litho in U. S. A.

TOWOLDMON0035667
WATER_PCB-00020136