

September 17, 1954
File: 411

O. W. Matheson - Manville

PREPARATION OF BLUE FIBER FOR NO. 83 SHEET PACKING
CP921-076

The original idea was to use Africa Norca Blue No. 300, as it is the cleanest of the African Blue fibers. Since this fiber was not available, the plant sent us CB300 Blue, which is somewhat similar to S Blue from Africa.

NC-3 MS
The method of processing consisted of the following:

1. A standard Johns-Manville willow, using the regular spring steel blades.
2. The speed was 1000 rpm, using a 75 hp motor.
3. The feed rate was kept at one ton per hour.
4. Any fines, such as dust, were collected in a baghouse.
5. Samples of the original fiber, and after each pass, were examined and compared with the specification, and also by Mr. H. J. Palumbo who is acquainted with the use of Blue in No. 83 sheet packing.



Specification Based upon Australian Blue Prepared by ACOA:

	<u>2M</u>	<u>4M</u>	<u>10M</u>	<u>Pan</u>	
Quebec Screen	4.0	10.0	1.0	1.0	
Wet Screen	+14M	+28M	+100M	+200M	-200M
	%	%	%	%	%
	30 to 50	0 to 13	0 to 16	0 to 16	36 to 56
					2 max.

Tests on Product Prepared by Research:

	Quebec Screen					Wet Screen				Rock
	2M	4M	10M	Pan		+14M	+28M	+100M	+200M	-200M
	oz	oz	oz	oz		%	%	%	%	%
Pass 1	9.9	4.0	0.7	0.7	55.9	8.4	8.0	5.1	22.6	20
2	11.6	2.8	0.7	0.7	49.5	5.8	10.4	9.5	24.8	12
3	13.1	2.1	0.7	0.7	48.8	8.5	9.5	7.8	25.4	8
4	14.6	0.8	0.7	0.7	50.7	8.7	9.8	8.4	22.4	5
5	14.0	1.6	0.2	0.2	50.2	7.6	9.2	7.8	25.2	3
Product from ACOA (Australian Blue)					38.4	4.2	6.2	4.4	46.8	3

Product Recovery:

Feed	CB300	2000 lbs
Fifth Pass:	Product shipped Gleason	55 bags at 50 lbs each
		2 bags at 40 lbs each
		1 bag at 30 lbs
	TOTAL	1860 lbs

Losses - Fines and Dusts 140 lbs or 7 per cent
Recovery 1860 lbs or 93 per cent



PLAINTIFF'S

September 17, 1954
Page No. 2
File: 411

Product Inspection

Each pass product was examined, and the data compared with the specification. It was not until the fifth pass that the product was sufficiently opened to be acceptable by Mr. Palumbo, as regarding the quantity of unopened bundles and rock. This number of passes would be considered out of reason and expensive, however, it will serve as a background on the amount of work necessary to prepare this grade of fiber when using existing willowing equipment.

We suggest that this fiber be used for making No. 83 sheet packing in order to determine the value of this product.

It is also possible that the number of willow passes may be considerably reduced if the quantity of crudy bundles do not need to be reduced to two per cent maximum

Recommendation:

We recommend that the next batch of fiber be selected from the NC300 shipment, and that this preparation be repeated. Also that when the next processed blue is used at the paper mill, that the beater will be lowered so as to brush out the unopened pencils that are not completely opened by the willowing process. If the beater roll could help brush out the fiber bundles, then the willowing process may be reduced to two.

M. S. Badollet
M. S. Badollet

vv

cc: R. H. North
J. Carlson
J. W. Riede
H. J. Palumbo
E. R. Williams
A. B. Cunningham
File: 411

