MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE 110789 LOT 33998

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
2714	1	T-278		
2576	1	T-209		
	STUMP			

TOTAL NET WT. 5290 PKG. N-CODE

PROD. SPVR.	DATE	WHSE. OPER.
JV	1/28/80	

CO 04 CODE KO-789-D PKG. ____

→ 1/28 ~~JAN 24~~ 33998

EST. WGT. ~~1199~~ 1032 LBS.

Full Rem

Total Weight 5199# (Req. _____)

PROCESSING INSTRUCTIONS: BATCH UNI

PROCESSES	APPROVED B
KO-789-D (I)	EWK 9-21-7
	DCG 9-21-7
	MTW 10-2-7

TYPED BY JJc 10-8-76

MAKING NOTES

REMARKS

NAME: "KROLOR" ORANGE Y NON-BLEEDING

INSTRUCTIONS

VAT	247			
DATE	1-25-80			
TIME	2:40 Am			
RELEASED BY	PCH			
PRESS	22	23	24	25
NO. OF CAKES	46	46	52	48

PRESS with AGITATION

WASH TO 5000 OHMS with 35-75°F water

TEST AFTER 6 HOURS

LOAD on 6 cars

TDS

SAMPLES 1 - 8 oz. jar

DELIVER TO CTL for color

-PRESSING- RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5T
STARTED	5PM				
CAKES USED	48				
WATER ON	1PM				
HRS. WASHED	6 HRS				
OHMS	5000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	7				

EXPLAIN LOSSES

SAMPLED BY RELEASED BY TDS

-DRYING-

DRY 16 HOURS AT 220°F L.V.

LUMP: OK - WET - SALTS - CONTAMINAT

No Record of and PROCESSING Ion

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 16

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT. 5367

SAMPLED BY RELEASED BY

-GRINDING-

MILL 938 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 210 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 Env. + 1 Pint Can

DELIVER TO CTL

DATE MIXED

SAMPLED BY RELEASED BY

DUP050095348

33998
41
252

0.00	*
3.17	+
0.14	-
3.13	+
0.14	-
3.02	+
0.14	-
3.24	+
0.14	-
3.14	+
0.14	-
3.06	+
0.14	-
3.06	+
0.14	-
3.25	+
0.14	-
3.02	+
0.14	-
2.97	+
0.14	-
2.94	+
0.14	-
32.46	*

32.46	+
3.15	+
0.14	-
2.96	+
0.14	-
3.13	+
0.14	-
2.95	+
0.14	-
3.04	+
0.14	-
3.11	+
0.14	-
2.80	+
0.14	-
52.62	*

DUP050095349