MD-3-A


PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Y7838 LOT E1833

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	12	2219	6	
	STUMP	Lemyo	2219	

TOTAL NET WT. 2219 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
	7.11	


0.T
197.+
175.+
186.+
197.+
209.+
168.+
173.+
181.+
210.+
194.+
189.+
140.+
2219.T

PRODUCT NAME = DALAMAR YELLOW

NON-BLEEDING PROCESSES — APPROVED BY
YT-858-D (X)
ALTERNATE
TYPED BY JMH

12

MAKING NOTES

CK 16 CODE YT-858-D PKG ____

LOT MAY -0-81- E1383

EST'D WGT 2313 LBS

TOTAL EST'D WGT= LBS (CRT ENTRY)

JOB NAME: 46YT858DPX

INSTRUCTIONS =					PRESSING = RECORD	1ST	2ND	3RD	4TH	5TH
VAT	106				PRESSLOAD					
DATE	5-18-81				STARTED	5A				
TIME	7:Pm				CAKES USED	64				
RELEASED BY	S.B.				WATER ON	PM				
PRESS	32	33	35		HRS. WASHED	4				
NO. OF CAKES	60	60	60		OHMS	6000				
PRESS WITHOUT AGITATION					HRS. WASHED					
WASH TO 4000 OHMS - 35-75 F WATER					OHMS					
TEST AFTER 6 HOURS					HRS. WASHED					
LOAD ON 10 CARS					OHMS					
DO NOT LOAD BOTTOM 2 ROWS OF CARS					CAKE CONDITION					
					NO CARS LOADED	6				
					EXPLAIN LOSSES					
					± 3" pumped on top of YT858 Lot E 1420					
SAMPLES JAR					SAMPLED BY					
DELIVER TO					RELEASED BY					

= DRYING =

DRY 36 HOURS AT 150 F

LUMP: - OK - WET - SALTS - CONTAMINATD

3 sacks pumped on top of Lot 1420 percentage for low yield

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS 13
LUMP WGT 2213

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY RH

= GRINDING =

MILL 4 OR 10HSP 1/8"RP SCRN 3500 RPM
MAX. TEMP. F

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV & 1 PT CAN
DELIVER TO CTL

DATE MIXED 5-21-81

SAMPLED BY 447
RELEASED BY

DUP050098614

1383
51
16

0.00 *

2.06 +
0.14
1.88 +
0.14
1.81 +
0.14
2.12 +
0.14
2.10 +
0.14
2.10 +
0.14
1.92
0.14
1.83 +
0.14
1.72 +
0.14
1.91 +
0.14
1.94 +
0.14
1.83 +
0.14
0.71 +
0.14
22.11 *

DUP050098615