

MOL

TALC PRODUCT SPECIFICATIONS
(If there are any exceptions to these specifications
they will be noted on the customer specification sheet).

Revised: 3-85
Revision: #6
Supersedes: 1-85

CONFIDENTIAL

Product Name	Prod. No.	Wet Test Grind	Hegman (Min.)	Tapped Density (lbs./cu. ft.)	Loose Density (lbs./cu. ft.)	Min. GEB	Max. Moist.	Max. Acid Soluble	Notes & Crude Blends
Altalc 200 USP	1835	98.0-98.6/200		60-66	28-32	86		2% as SO ₄	100% Montana cosmetic crude (including Barretts)

* Specially Treated, Low Microorganism
** Must be USP Certified

PLAINTIFF'S
EXHIBIT
CAM-191

ITA-LG 00317

Product Name	Prod. No.	Wet Test Grind	Hegman (Min.)	Tapped Density (lbs./cu. ft.)	Loose Density (lbs./cu. ft.)	Min. GEB	Max. Moist.	Max. Acid Soluble	Notes & Crude Blends
Mistron Vapor	0007	99.95/325 Min.	5.5			85			100% BY 80
Monoblend	1765	98.0-98.5/200		61-63	24-26	85			60% Beaverhead + 40% Italian
*Olympic	1515	98.8-99.2/200		59-66	23-26	86			100% Beaverhead

* Specially Treated, Low Microorganism

Product Name	Prod. No.	Wet Test Grind	Hegman	Tapped Density (lbs./cu. ft.)	Loose Density (lbs./cu. ft.)	Min. GEB	Max. Moist:	Max. Acid Soluble	Notes & Crude Blends
*Supra	1705 1700	98.0-98.5/200		57-59	23-25	86			100% Italian

* Specially Treated, Low Microorganism