PLAINTIFF'S EXHIBIT

GP-500

PAOLI LABORATORY FEBRUARY 15, 1962 BLUE RAPIDS, KANSAS

MR. J. R. TATT ASBESTOS

J. D. RAUCH - bjm

We have enough 7-D Asbestos in stock to formulate approximately 95 tons of Acoustical Plaster, however we have completely depleted our inventory of 7-M Asbestos as used in Patching Plaster 962 and Certflor 843. Since we have such a large inventory of 7-D Asbestos would it be possible to substitute 7-D for 7-M in either or both the 962 and 843 formulas or should we re-order the 7-M Asbestos? Please advise.

PRINTED IN U. S. A.

Bestwall Gypsum Company

962 File

FOR BLUE RAPIDS DATE Feb. 20, 1962 FROM Paoli Lab OFFICE

ATTENTION OF Mr. J. D. Rauch SUBJECT ASBESTOS

ANSWERING YOURS 2/15/62 DICTATED BY J. R. Watt/md

-1/

It will be satisfactory to substitute 7-D asbestos for 7-M in patching plaster. This fiber is a little longer than 7-M, so be sure the patching plaster is mixed amply long to completely disburse the fibers.

Sales no longer carries Certflor 843 in their line, so this formula is being cancelled.

