

Durafilm Gloss
Interior Gloss
White
I.G.W.
First

				Actual 3/31/42		Market 3/31/42	
<u>Pigment</u>							
461-S	Lithopone	2520	70.56	3.95	99.54	4.40	110.88
2030-T	Titanium Oxide	600	18.54	14.87	89.22	14.80	88.80
547	Aluminum Stearate	12	1.32	25.22	3.03	25.00	3.00
<u>Vehicle</u>							
(48)	Bodied Linseed Oil	894	111.75	14.75	131.87	17.22	153.95
(2325)	Bod. Dehydrtd Castor O.	504	64.06	17.73	89.36	19.08	96.01
(2957)	Mixing Varnish	1116	146.31	13.66	152.45	15.19	169.52
(348)	Mineral Spirits	1236	184.54	1.55	19.16	1.50	18.54
(440)	Drier	114	15.00	5.68	6.48	6.23	7.10
(152)	Drier	24	3.31	13.66	3.28	14.32	3.44
(1767)	Anti-Skinning Agent	18	2.67	5.79	1.04	5.74	1.03
				<u>595.43</u>		<u>652.27</u>	
				98.36		107.75	
Unrelated Total				618.06			
Factor				2.05%			
Total Yield				605.38			
<u>Analysis</u>							
Total Yield per						.984	
Total Yield per						.018	
Total Yield per						.039	
Total Yield per						1.041	
Total Yield per						.187	
Total Yield per						1.228	
Total Yield per						1.321	