

Lucasal Enamel Undercoat
Enamel Undercoater
White
R.P.W.

		Actual 3/31/42		Market 3/31/42	
Pigment					
2233-M	Titanium Oxide	1002	28.687	14.87	149.00
461-S	Lithopone	2754	77.112	3.95	108.78
20-RO	Magnesium Silicate	402	16.924	0.96	3.86
1817	Trtd. Calc. Carbon.	396	17.939	1.70	6.73
Vehicle					
(629)	Grind & Mix. Veh.	2184	297.898	10.29	224.75
(48)	Bodied Linseed Oil	162	20.250	14.78	23.90
(440)	Drier	114	18.002	5.68	6.48
(152)	Drier	18	2.482	13.66	2.46
(348)	Mineral Spirits	618	92.267	1.66	9.58
(141)	Kerosene	324	48.266	1.01	3.27
(1767)	Anti-Skinning Agent	30	4.443	5.79	1.74
				540.83	577.93
		8004	621.240	88.25	94.36
			621.240		
			1.415		
			612.80		
				.883	.94
				.018	.01
				.042	.04
				.943	1.00
				.187	.18
				1.130	1.19

C.I.	L.C.D.
2.23	2.35
1.89	1.99
2.23	3.50
	2.35
	2.47

OVER 500
UNDER 500

OPA ■■■000762

N 4769