

- 51 -

FORMULAE OF SPECIAL PAINTS AND VARNISHES
Produced by Three Manufacturers in Chicago, January 1941 - June 1942

WILLIAMS, W. J. 2/

Outside White House Paint (W.F.C.M.)

Percentage Formula : Working or Vat Formula

January 1941 to June 1942 2/

January 1941 to June 1942

<u>Percent</u>		<u>Gals.</u>	<u>Lbs.</u>
60.1	Standard Zinc		300
	Sublimed White Lead		350
	Titanium Oxide		30
39.9	Asbestos		130
100.0	Marytes		170
	Ultramarine Blue	3 av. oz.	
	Bleached Linseed Oil	70	
	Clean Spirits	5	
	Intense Drier	4	
	Solution	2	

Inside Flat White Paint (#468)

Percentage Formula : Working or Vat Formula

January 1941 to June 1942 2/

January 1941 to June 1942

<u>Percent</u>		<u>Gals.</u>	<u>Lbs.</u>
61.3	Lithophone		600
	Surfox		200
	Asbestos		150
38.7	Aluminum Stearate		3
100.0	Hydroquinone	2 av. oz.	
	Heavy Grinding Oil	7	
	Bleached Linseed Oil	13	
	Flat Paint Grinding Varnish	14	
	Clean Spirits	40	
	Soligen Lead Drier	4	
	Cobalt Drier	2	
	Bodying Varnish	1/2	

W. J. Williams stated that there were no changes in his formulae for the products from January 1941 to June 1942, except those shown for enamel.

W. J. Williams working formula.