

TOTAL EST'D WGT= LBS (CRT ENTRY)

PROCESSES APPROVED BY
YE-698-D (S) F. POST 1/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS

PRESSING

RECORD

VAT				
DATE				
TIME				
RELEASED BY				
PRESS	2	92	93	
NO. OF CAKES	54	54	54	
PRESS WITH AGITATION				
WASH TO 2000 OHMS WITH 35-75 F WATER				
TEST AFTER 2 HOURS				
LOAD ON 7 CARS				

	1ST	2ND	3RD	4TH	5TH
PRESSLOAD					
STARTED	4:15 PM				
CAKES USED	54				
WATER ON	6:15 PM				
HRS. WASHED	2				
OHMS	3000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO CARS LOADED	6				
EXPLAIN LOSSES					

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

== DRYING ==

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY
RELEASED BY, *SG*

NO DRUMS 18
LUMP WGT 5842

= GRINDING =

MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT 19" FOR
HIGH AIR FLOW

SCREEN:	RPM
MAX. TEMP.	F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

1445
41
17

0.00 *

3.44 +
0.12 -
3.39 +
0.12 -
3.40 +
0.12 -
3.50 +
0.12 -
3.44 +
0.12 -
3.41 +
0.12 -
3.48 +
0.12 -
3.49 +
0.12 -
3.45 +
0.12 -
3.26 +
0.12 -
3.25 +
0.12 -
3.19 +
0.12 -
3.27 +
0.12 -
3.41 +
0.12 -
3.38 +
0.12 -
3.22 +
0.12 -
3.25 +
0.12 -
3.35 +
0.12 -
58.42 *