MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE RT-695T LOT 369324

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
	7	948	028	

STUMP Lungs

TOTAL NET WT. 948 PKG. N–CODE

PROD. SPVR. DATE 10/10/80 WHSE. OPER. 23

DUP050107240

36/180

CG 36 CODE RT-695-D PKG. ____

→ AUG·27·80 36924

EST. WGT. 1350 LBS.

SPLIT-OFF: 21# TO LOT 00221 FIRED while grinding.

9 FIRE BATCH 9/8/80

AUG 22 1980

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
RT-695-D (M)	DCG 1-12
	IHD 2-25
TYPED BY	
LG 5-15-72	

~~Retyped 2-27-80~~ MnM

MAKING NOTES

REMARKS

NAME: BON RED DARK

NON-BLEEDING

-PRESSING-

INSTRUCTIONS

VAT	100				
DATE	8-28				
TIME	1100 A				
RELEASED BY	JDC				
PRESS	32	33	35 (36) 30	38	39
NO. OF CAKES	60	60	60	60	60

PRESS Without AGITATION

WASH TO 4000 OHMS with 35-75F water

TEST AFTER 16 HOURS

LOAD on 8 cars

SAMPLES

DELIVER TO

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	3:30 PM				
CAKES USED	30				
WATER ON	10:31 PM				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	4				

EXPLAIN LOSSES

SAMPLED BY RELEASED BY

-DRYING-

HOURS Dry 24 hours at L.V. H.V.

TEMP. 180 °F °F

SE 15-30

Mn Color

SAMPLES

DELIVER TO

LUMP: - OK - WET - SALTS - CONTAMINATED

No record of any processing losses can not explain low yield

ADDITIONAL DRYING HOURS REQUIRED

Drums 6

NO. CARS PULLED LUMP WGT. 1184

SAMPLED BY RELEASED BY RH

-GRINDING-

MILL 5 HSP 1/8" RP SCREEN 4600 RPM

MAX. TEMP. °F

Mn Color

SAMPLE AFTER / WITHOUT MIXING

SAMPLES 1-Env & 2 pt cans

DELIVER TO C T L

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY 149. 9/4/80 RELEASED BY

DUP050107241



DUP050107242