

Cross Index:
1017-C
KW-3406

C - 4

CC: Mr. C. R. E. Merkle, Lab.
Mr. J. W. Iliff, Lab.
Mr. H. R. Young, Lab.
Dr. A. J. Hemmer, Plant
Mr. J. P. Elliott, Wilm.D-8026

Philadelphia Laboratory
February 21, 1946

RETURN TO MARSHALL LABORATORY LIBRARY

MEMORANDUM REPORT #M-28

REFERENCE COPY

KW-3406 "TI-PURE" LW NOT FOR CIRCULATION

Ten tons of "Ti-Pure" LW were purchased from the Riegel Paper Company in order to extend our titanium supply. This material is titanium directly out of the calciner and ground, is unwashed and contains between 1/4 and 1/2% soluble salts. It is the anatase type.

We have established temporary formulas in the 596 Line bases, substituting KW-3406 for W-28. The bases involved are 596-858, -874, -987, -996, -8014, -8062. These bases will be used principally in 409-861 Semi-Gloss White, 409-801 High Hiding Mill White, 479-767 Ovalite Undercoater and 479-760 Primer-Sealer. Substitution was made on an equal hiding, equal volume ratio. For details see Notebook 2936, pages 66-77.

PHILADELPHIA LABORATORY

G. H. Wescott
G. H. WESCOTT

CHW:MEH