RECEIVED

JAN 8 19

HASKELL LABORATORY

DON'T SAY IT—WRITE IT

DATE 1/3/68

TO R.S. WARITZ

AT HASKELL LAB

FROM H.H. FANNING — MARSHALL LAB

TOXICITY STUDY - URETHANE ENAMELS

MR 1172-1

HERE IS REMAINDER OF COMPOSITION INFORMATION ON THE U.S. PAINT "ALUMIGRIP" POLY URETHANE ENAMEL SYSTEM.

(AA 92-R-1) ENAMEL # 2099 RED BASED ON "DESMODIEN" 650 RESIN

PIGMENT	26.8%
BINDER	32.2%
VOLATILE	41.0%
	100.0% BY WT

VOLATILE:

14.2%	ETHYL ACETATE
3.0%	TOLUENE
23.8%	CELLOSOLVE ACETATE
41.0%	

(AA-92-C-5) ~~CATALYST~~ # FOR AA-92-R-1 ENAMEL

BASED ON "DESMODUR" N RESIN

BINDER SOLIDS	40.0% BY WT
VOLATILE	60.0% BY WT
	100.

VOLATILE:

18.0%	ETHYL ACETATE
10.2%	TOLUENE
6.8%	XYLENE
25.0%	CELLOSOLVE ACETATE.
60.0%	

PLEASE LET ME KNOW IF I CAN BE OF FURTHER HELP.

PHONE 197-426.

REGARDS—

Herb Fanning

DUP040000810