



AROCLORS •

#-241-

As Used in Chlorinated Rubber

Monsanto Technical Bulletin No. P-124

January 1, 1948

Monsanto Chemical Company, St. Louis 4, Mo.

* * * *

AROCLORS, chlorinated biphenyl and chlorinated poly-phenyls, are effective plasticizers and resins for chlorinated rubber base lacquers, varnishes and paints.

These protective coatings are used where flame resistance, corrosion resistance, chemical resistance, i.e., resistance to acids, alkalis and water, and good electrical insulating properties are required.

Some of the important applications for these protective and decorative coatings for wood, metal, brick, stone, concrete and fabric surfaces include:

1. Wood and metal used in the construction of yachts, barges and other marine craft.
2. Structural steel for bridges, buildings, roofs and power-line structures.
3. Structural materials used at chemical plants, pulp and paper mills, textile mills, petroleum refineries and gas works where protection against acid fumes, alkalis and gas is essential.
4. For the protection of tank cars and other rolling stock and construction machinery against corrosive materials and weathering.
5. To protect equipment used in electroplating and as stop-off lacquers in this industry.
6. Masonry floors and walls. Concrete swimming pools and traffic paints.
7. As cable coatings requiring nonflammability, chemical resistance, water resistance and excellent electrical properties.
8. Coatings for cloth to impart "waterproofing" qualities as well as chemical and flame resistance.

*AROCLOR-Reg. U.S. Pat. Off.

* * * *

The information contained in this bulletin is, to our best knowledge, true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. The Monsanto Chemical Company disclaims any liability incurred in connection with the use of these data or suggestions. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in contact with existing patents covering any material or its use.

AROCLORS As Used in Chlorinated Rubber

{ MONSANTO TECH. BUL. No. P-124
JANUARY 1, 1948

0514398

TOWOLDMON0035877

MIXED SOLVENTS

70 : 30	Acetone : hexane
97 : 3	Acetone : mineral spirits
83 : 17	Benzene : isopentane
41 : 7 : 35 : 17	Cellosolve : ethanol (anhydrous) : ethyl acetate : xylene
30 : 70	Cellosolve : turpentine
18 : 59 : 23	Cellosolve : turpentine : mineral spirits
64 : 36	Ethyl acetate : isopentane
30 : 30 : 40	Ethyl acetate : isopropyl acetate : Troluol
40 : 60	Methyl isobutyl ketone : Troluol
30 : 70	Hi-Flash solvent naphtha : turpentine
70 : 30	Methyl acetate : isopentane
85 : 15	Shell TS-28 : xylene

IV. AROCLOR AND CHLORINATED RUBBER, PLASTICS FILMS

The resinous Aroclors 1262 and 5460 show good miscibility with chlorinated rubber films as laid down from toluene solution containing 20 per cent of the plastics, using 2 : 1 and 1 : 1, Parlon : resin, ratios. Similarly, the plasticizer type Aroclor 1242, 1254 and 1260 show good miscibility in chlorinated rubber.

The properties of films derived from the following formulations containing either Parlon and resinous Aroclors 1262 or 5460, or Parlon and the plasticizer type Aroclors 1242, 1254 or 1260 were studied.

RESINOUS TYPE AROCLOR FOR PARLON PLASTICS

Ingredients	Parts by weight				
Parlon, 20-cp.	16	16	16	12	12
Aroclor 5460	8	8	8	12	12
Dibutyl phthalate		4			3
Tung oil, Thermolyzed, 976			5		3.75
Xylene or butyl acetate	76	72	71	76	72.25

PLASTICIZER TYPE AROCLORS FOR PARLON PLASTICS

Ingredients	Parts by weight	
Parlon, 20-cp.	20	20
Aroclor 1254 or 1260	4	20
Xylene	76	70

Examination of the films cast from these lacquers revealed the following characteristics imparted by the Aroclors:

Adhesion:—Unplasticized chlorinated rubber films have very poor adhesive qualities. The lacquer film containing Aroclor 5460 gave good adhesion to aluminum, bare steel, primed steel, galvanized iron and Transite surfaces. Other commercially available resins, particularly oil modified alkyd resins, tested in similar films gave better adhesion than Aroclor 5460 to such surfaces as glass, tin, copper, sealed wood and cellophane.

The lacquer films plasticized with Aroclors 1254 or 1260 gave good adhesion to Transite, cellophane, galvanized iron and primed steel surfaces. Some of the other commercially available plasticizers tested in similar films gave better adhesion than the Aroclors to aluminum, tin, bare steel, copper and sealed wood surfaces.

Aroclors, alone, possess pronounced adhesive qualities. Doubtless, where the objective is to produce adhesives, by varying the Aroclor content or by using a mixture of Aroclors in the chlorinated rubber lacquers, much better adhesion to all of the surfaces would be accomplished than was the case with the type of plastics films studied.

Resistance to Aqueous Solutions:—Aroclors 1254 or 1260 used as plasticizers and Aroclor 5460 used as a resin in chlorinated rubber produced plastics films possessing satisfactory resistance to 10 per cent hydrochloric acid, 5 per cent sodium hydroxide, 5 per cent sodium chloride solutions and to water spot tests.

Film Hardness:—Using Aroclor 5460 in ratios of 5 : 10 and 10 : 10, Aroclor : Parlon, decidedly softer films were produced than when other commercial resins were similarly used. Likewise, Aroclors 1254 or 1260 used in ratios of 2 : 10 and 5 : 10, Aroclor : Parlon, gave softer films than obtained from other commercial plasticizers, used at these concentrations. This indicates the strong plasticizing action of these Aroclors on chlorinated rubber.

Cold-Check Resistance:—Regarding cold-check resistant qualities imparted to chlorinated rubber films, Aroclor 5460 is somewhat superior to Bakelite type resins, but not as good as long-oil modified alkyds. Aroclor 1260 used as a plasticizer rates, in terms of cold-check resistance, somewhat better than Aroclor 1254 and nearly as good as the best of the other plasticizers studied for this property.

Miscellaneous Properties:—Parlon plastics films containing Aroclors 5460, 1254 or 1260 have entirely satisfactory sanding and polishing characteristics.

Weatherability:—Pigmented chlorinated rubber finishes containing Aroclors have consistently shown good outdoor weatherability. However, similar unpigmented finishes, regardless of the plasticizer or resin used and also in the absence of these additives, have been found to give poor outdoor weathering. Relatively poor resistance to ultraviolet light is a weakness of chlorinated rubber.

Most pigments, with the exception of ultra-marine blue are usable with Parlon finishes and are recommended when the coating is to be subjected to outdoor weathering or exposed to ultraviolet light. However, there is considerable variation regarding the protection offered by different pigments. Inspection of Parlon-fortified alkyd enamels showed the weatherability varied from 63 months for the enamel pigmented with chrome green to 4 months for enamel pigmented with a titanium dioxide-iron blue combination.

V. USES FOR AROCLORS IN CHLORINATED RUBBER COATINGS

A. Finishes for Alkaline Surfaces:

Aroclors, as well as chlorinated rubber, are highly resistant against alkalies and moisture. Because of these properties paints based on Aroclor and chlorinated rubber combinations are used in large quantity for application to concrete floors, walls, swimming pools, etc. Examples of this type of paint are given in Table IV.

TABLE IV. AROCLOR PLASTICIZER IN CHLORINATED RUBBER PAINTS
FOR ALKALINE SURFACES

(Examples of starting formulas)

Materials	Formula 1 for basement floors	Formula 2 to meet Fed. Spec. TT-P-91 (Parts by weight)	Formula 3 for swimming pools
Parlon, 20-cp. type	18	18	14.6
Aroclor 1254	10	10	4.4
Rezyl 869	8		
Aroclor 5460 or Cumar Pro		6	
Beckosol 31			2.9
Tung oil, Thermolyzed, 976			4.4
Titanium dioxide	16	16	19.7
Zinc oxide	2	2	6.5
Silica flour	3		
Carbon black	0.2	0.5	
Xylene	42.8	47.5	
Hi-Flash naphtha			47.5
Totals	100	100	100

B. Acids and Alkali-Resistant Finishes:

Particular care must be exercised in the choice of resins and plasticizers for use in chemical resistant paints. For this purpose, Aroclors are outstanding and are being used successfully in the acid and alkali-resistant chlorinated rubber formulations given in Table V.

TABLE VII. RESINS AND PLASTICIZERS MISCIBLE IN PARLON

RESINS

Amberol 801, 806P, ST-137, F7	Formvar
Aroclor 1262, 5460	Gelva 2.5
Aroplaz 920, 930, 935, 940	Glyptal 1247, 2450, 2454, 2458, 2464, 2466, 2500
Bakelite XR-3180, XR-4503, XR-4006, BR-2963, XJ-9868, BR-1329, BR-3360	Lewisol 2L, 28, 33
Beckacite 1112	Methyl Methacrylate Polymers
Beckamine P-138, P-254	Neville R-3, R-10
Super-Beckamine 3501	Pentalyn A, G, M, X
Beckopol 1400	Petrex 1, 130H
Beckosol 1 (solid), 18, 31, 34, 40, 1329	Phenac 633-M
Beetle Resin 227-8	Rezyl 116, X315, 412, 775, 803, 807, 829, 869, 880, 1103
Clorafin 70	Rosin
Copal	Santolite MHP
Cumar P10	Staybelite Ester 1, 2, 10
Dammar	Staybelite resin
Duraplex C-45-LV, C-48, C-49, C-50-LV, C-51, C-62, D-61, D-62, E-71, E-71-A, E-73	Super-Beckacite 1001
East India gum	Syntex H1, H3, H12, 17, 213, 22, 28, 29, 32, 36
Ester gum	Teglac 15, Z-152
Ethyl Methacrylate	Velsicol AD6-3
Esterol 750	Vinsol

PLASTICIZERS

Amylchloro naphthalene	Methyl cellosolve oleate
Amyl oleate	Monoamyl naphthalene
Amyl stearate	Naftolen
Aroclor 1242	Neville heavy oil No. 2
Aroclor 1254	Nevillite oil
Aroclor 1260	Oiticica oil
Butyl myristate	Palm fatty acid esters
Butyl stearate	Perilla oil
Camphor	Polyamyl naphthalene
Castor oil, raw	Resinous Products C-24
Castor oil, dehydrated	Santicizer B-16
Castor oil fatty acid esters	Santicizer M-17
Cellosolve phthalate	Sextol phthalate
Coconut fatty acid esters	Sextol stearate
Diamyl naphthalene	Soya bean fatty acid esters
Diamyl phthalate	Soya bean oil
Dibutyl phthalate	Thermoil A
Dibutyl sebacate	Tributyl phosphate
Diethyl phthalate	Tricresyl phosphate
Dimethyl phthalate	Triethyl citrate
Fish oil	Triphenyl phosphate
Hercolyn	Tung oil, Thermolyzed, 976
Linseed oil	

The strong points and limitations of the resins and plasticizers given in Table VII relative to the properties they impart to chlorinated rubber are known. None give the important over-all desired qualities attained by the use of Aroclors. If occasion arises to consider the use of these materials in specific applications for chlorinated rubber, then more detailed information about them will be given.

The Aroclor compounds impart the following advantages to the films cast from these lacquers:

Adhesion

Unplasticized chlorinated-rubber films have very poor adhesion. The lacquer film containing Aroclor 5460 adheres well to aluminum, bare-steel, primed steel, galvanized iron, and Transite surfaces. The lacquer films plasticized with Aroclor 1254 or 1260 give good adhesion to Transite, cellophane, galvanized iron, and primed-steel surfaces.

Though compounds with an Aroclor alone possess pronounced adhesion qualities, better adhesion to all of the surfaces results if mixtures of Aroclor or varied contents are used.

Resistance to Aqueous Solutions

Chlorinated-rubber films with Aroclor 1254 or 1260 (plasticizers) and Aroclor 5460 (resin) show satisfactory resistance to solutions of 10-per cent hydrochloric acid, 5-per cent sodium hydroxide, 5-per cent sodium chloride, and water-spot tests.

Film Hardness

Softer films are produced with Aroclor 5460 in ratios of 5:10 and 10:10 (Aroclor and Parlon) than with other commercial resins in similar mixtures. Likewise, softer films result from Aroclor 1254 or 1260 in ratios of 2:10 and 5:10 (Aroclor and Parlon) than with other commercial plasticizers at these concentrations. These tests show that Aroclor compounds have strong plasticizing action on chlorinated rubber.

Cold-Check Resistance

Aroclor 5460 is superior to phenol-formaldehyde resins in cold-check resistance imparted to chlorinated-rubber films, but not as good as long-oil-alkyd modification. Aroclor 1260 is a somewhat better plasticizer than Aroclor 1254.

Weather Resistance

Pigmented chlorinated-rubber finishes containing Aroclor have consistently withstood outdoor weather tests, but unpigmented finishes do not weather well regardless of the resin or plasticizer used.

Poor resistance to ultraviolet light is also a weakness of chlorinated rubber. Most pigments (except ultramarine blue) are usable with Parlon and are recommended if the coating is to be subjected to outdoor weather or ultraviolet light. However, pigment protection varies considerably. Inspection of alkyd enamels fortified with Parlon showed weatherability varied from 63 months with chrome green to 4 months for titanium dioxide-iron blue combinations.

Sanding and Polishing Properties

Plastic films compounded with Parlon and Aroclor 5460, 1254, or 1260 have showed satisfactory sanding and polishing characteristics.