MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY787 LOT 34722

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
1,702	1	T — 194		
1,766	1	T — 135		
	STUMP			

TOTAL NET WT. [illegible] PKG. N--CODE

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	3/1/80	

N 2628

22/243

CG 03 CODE KY-787-D PKG. ____

→ MAR-5 34722

EST. WGT. ~~1090~~ 990 LBS.

OK / AP

Total Wgt. ~~3490#~~ 3390

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (R)	FWK 9/22/76
Alternate	DCG 9/27/76
TYPED BY	
NE 2/12/77	

MAKING NOTES

REMARKS

NAME: KROLOR - YELLOW MEDIUM NON-BLEEDING

INSTRUCTIONS -PRESSING- RECORD

						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
VAT	243					STARTED	6AM				
DATE	3-8-80					CAKES USED	46				
TIME	12:30 AM					WATER ON	13 hours				
RELEASED BY	[illegible]					HRS. WASHED	4				
PRESS	22	23	~~24~~	24		OHMS	3600				
NO. OF CAKES	46	46	~~46~~	52		HRS. WASHED					
PRESS with		AGITATION				OHMS					
WASH TO 2000		OHMS with 35-75°F water				HRS. WASHED					
TEST AFTER 2		HOURS				OHMS					
LOAD on 6 cars						CAKE CONDITION					
						NO. CARS LOADED	6				
						EXPLAIN LOSSES					

SAMPLES 1-8 oz JAR
DELIVER TO ctl for color

SAMPLED BY [illegible] RELEASED BY [illegible]

-DRYING-

Dry 12 hrs at 220°F.
Then Dry 8 hrs at 160°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

No. Drums 14

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 3411
SAMPLED BY RELEASED BY [illegible]

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 ENV & 1 Pt. can
DELIVER TO CTL

DATE MIXED

SAMPLED BY RELEASED BY

DUP050093687

N 26283.01

34722
4100
18

0.00	*	
2.59	+	
0.14	-	
2.71	+	
0.14	-	
2.61	+	
0.14	-	
2.66	+	
0.14	-	
2.66	+	
0.14	-	
2.65	+	
0.14	-	
2.70	+	
0.14	-	
2.61	+	
0.14	-	
2.43	+	
0.14	-	
2.60	+	
0.14	-	
2.71	+	
0.14	-	
2.56	+	
0.14	-	
2.67	+	
0.14	-	
1.91	+	
0.14	-	
34.11	*	

DUP050093688