


MD-3-A 16

PACKAGE TICKET

CODE RT795 LOT K2K 53

PO	NET WT/PKG.	NO. PKG.	PACK WT.	LOCATION
		14	2379	34


STUMP

TOTAL NET WT. 2379

LUMP WT. 2428 PKG. N-CODE

PROD. SUPV. RP DATE 10 25 82 OPERATOR 23

DUP050103115


0・C
1・89 +
2・09 +
1・71 +
1・70 +
1・49 +
1・53 +
1・69 +
1・73 +
1・77 +
1・81 +
1・71 +
1・85 +
1・76 +
1・06 +
014
23・79 T

CG 16 CODE 795 RT-~~95~~-D PKG. ____

→ OCT. 19 K2K53

EST. WGT. 2589 LBS.

33/280

14

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
RT-795-D (M)	BBK 10-19-77
Alternate	DCG 10-28-77
TYPED BY	
JLC 11-7-77	

MAKING NOTES

REMARKS

NAME: MONASTRAL® ~~RED~~ VIOLET R NON-BLEEDING

INSTRUCTIONS					- PRESSING - RECORD					
VAT	280				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	10-19-82				STARTED	5PM				
TIME	932PM				CAKES USED	60				
RELEASED BY	SF				HOURS TO FILL					
PRESS	13/14	15/16	38	39	33 60					
NO. OF CAKES	6 x 42	6 x 42	60	60						
PRESS WITH		AGITATION								
WASH TO	-	OHMS								
TEST AFTER	-	HOURS								
LOAD	ON 8 CARS									
					CAKE CONDITION					
					NO. CARS LOADED	10				
					EXPLAIN LOSSES					
SAMPLES										
DELIVER TO					SAMPLED BY		RELEASED BY			


- DRYING -

DRY 20 HOURS AT 220°F	LUMP: - OK - WET - SALTS - CONTAMINAT
	DRYER SECTIONS:
	ADDITIONAL DRYING HOURS REQUIRED
	NO. DRUMS 11
SAMPLES	NO. CARS PULLED LUMP WGT. 2423
DELIVER TO	SAMPLED BY RELEASED BY

- GRINDING -

MILL 1 HSP 0.066 RP SCREEN 3480 RPM	SCREEN RPM
MAX. TEMP. 140 ~~F~~ °F	MAX. TEMP. °F
Dry mix with CO2 when grinding up to pH 8 a.f. Dalyl3	EXPLAIN LOSSES
SAMPLE WITHOUT MIXING	DATE MIXED 10-25-82
SAMPLES 1 Env + 1 Pint Can	
DELIVER TO CTL	SAMPLED BY 389 RELEASED BY

DUP050103117



DUP050103118