

June 20, 1972
RM Spec. No. 18
NEW

PLAINTIFF'S EXHIBIT

GP-1474

ASBESTOS SG 210

DESCRIPTION: - Short fibered grit free asbestos

USE: - Ingredient in joint compounds

SOURCE: Union Carbide Corp.

SPECIFICATIONS: - Should be free from gritty particles. Test for grit is
GRIT made by decantation with water, using a 25 gm sample and an
800 or a 1000 cc beaker. Not less than 750 cc of water shall
be used for the first washing, so that any grit present will
settle freely and not be held in suspension. 0.1% fine
grit permitted.

FINESS: - U.S. Sieve Series

Through	8 mesh	- 100%
"	16 mesh	- 99.5 to 100
"	20 mesh	- 99 to 100
"	30 mesh	- 97 to 100
"	50 mesh	- 50 to 90
"	100 mesh	- 0 to 50

For fineness test, use a 50 gm sample and shake for 30 mins.
on the Ro-Tap.

WATER TO TC: - 380-420

COLOR: - White

SAMPLING: - Representative samples shall be taken from each shipment
for test. If the asbestos is ununiform in screen test
and water carrying capacity, it shall be blended by any
suitable method.

REMARKS: Tests on each carload of asbestos floats shall be compared
with tests of original shipment from same supplier, which was
found satisfactory. If any of the tests indicate doubt as
to its suitability for use in joint finisher, it shall be
tested in a laboratory batch. If this test shows the material
to be unsatisfactory, the shipment shall be rejected.

HANDLING PRECAUTIONS: - A dust mask should be worn when handling this raw material.
Spilled material should be promptly removed.

EDO:elz

SGP 0015902