

INTER-OFFICE MEMO **TENNECO CHEMICALS, INC.**

TO H.B. Carr AT Burlington DATE April 25, 1973
 FROM F.W. Kanzler AT Burlington COPY TO File
 SUBJECT Stoney-Mueller Plasticizers

Reference: Memo M. Greifeld from
 T. Noone, dated 4/9/73

The samples submitted were analyzed in Burlington and showed the following results:

<u>Sample Identification</u>	<u>Analytical Number</u>	<u>% Contamination</u>		<u>Refractive Index</u>	
		<u>Results</u>	<u>Spec</u>	<u>@ 25°C</u> <u>Results</u>	<u>Spec</u>
DOP UC	8777	*	<0.5%	1.4856	1.4845- 1.4858
DOP S-M	8778	2.02 DIDP	<0.5%	1.4854	1.4845- 1.4858
DIDP UC	8780	<0.01 DOP	<0.5%	1.4844	1.479- 1.487
DIDP S-M	8779	0.28 DOP	<0.5%	1.4843	1.479- 1.487

*No unusual impurities, other than typical for DOP, were found in this sample.

On the basis of the above, the Stoney-Mueller DOP must be considered to be out of specification.

Fred W. Kanzler
 F.W. Kanzler

Attachment.

FWK/jst