

BRAND NAME	INGREDIENTS	FORMULA IN LBS			YIELD IN GALS			UNIT COST PER POUND OR GAL			TOTAL COST OF INGREDIENTS		
		Before Change	After Change		Before Change	After Change		Before Change	After Change		Before Change	After Change	
SUPER OUTSIDE WHITE	Ti-Sil	255	255		9.8	9.8		.0575	.0575		15.30	15.30	
	35% Leaded Zinc	357	357		7.3	7.3		.07	.07		24.99	24.99	
	White Lead Carbonate	179	179		3.2	3.2		.0825	.0825		13.77	13.77	
	Refined L O	418.5	209.25		54	27		.161	.161		67.38	33.69	
	Bodied L O Z-6	---	83.7		---	9.3		.171	.171		---	14.33	
	Mineral Spirits	---	125.6		---	19.3		.017	.017		---	2.13	
	Liquid Driers	41.25	41.25		5.5	5.5		.0677	.0677		2.89	2.89	
	Calculated Yield	1250.75	1250.8		79.8	80.4		---	---		---	---	
	Material Cost Per Gal	---	---		---	---		---	---		1.56	---	
	L O Content per Gal	---	---		---	---		---	---		---	3.73	
CHILTON OUTSIDE WHITE	Zinc Oxide	400	400		8.5	8.5		.0725	.0725		29.00	29.00	
	White Lead Carbonate	410	410		7.3	7.3		.0825	.0825		33.83	33.83	
	Asbestine	150	150		6.5	6.5		.01	.01		1.50	1.50	
	Refined L O	589	299.5		76.0	38.3		.161	.161		94.83	48.22	
	Bodied L O Z-6	---	93.25		---	11.73		.171	.171		---	15.98	
	Mineral Spirits	---	125.6		---	23.1		.017	.017		---	2.56	
	Liquid Driers	52.5	75.0		7.0	10.0		.0677	.0677		3.68	7.50	
	Calculated Yield	1601.5	1578.5		105.3	105.4		---	---		---	---	
	Material Cost Per Gal	---	---		---	---		---	---		1.55	1.32	
	L O Content per Gal	---	---		---	---		---	---		---	3.74	

REPRODUCED AT THE NATIONAL ARCHIVES

OPA 26008

N 4406