# VISCOSITY WORK SHEET

| | | |
|---|---|---|
| Item 2746 | P.T.No. | Date 4-14-55 |
| Worker L. Kay | Polymer Lucite | Solvent EDC |
| For BENJAMIN | Charge 1270 | Temperature 25°C |
| Viscometer No. III | Efflux Time 248.3 | Weight: Gross 3.6283 |
| Viscometer No. A | Efflux Time 288.6 | Tare 3.5033 |
| Viscometer No. | Efflux Time | Net 0.1250 |

| Sample | Flask | Visc. No. | Solution Efflux Times | Rel. Inh. visc. Visc. | or M.W. |
|---|---|---|---|---|---|
| 4122-69-1 | H-9 | III | 335.2; 335.3; 335.2 | 1.349 | 165,000 |
| | 97 | A | 390.2; 390.3; 390.3 | 1.352 | 167,000 |

PC-1

N38718