

Bestwall Gypsum Company

FOR GRAND RAPIDS DATE Sept 1, 1961 FROM Paoli Lab OFFICE
ATTENTION OF Mr. J. B. Moss SUBJECT SPECIAL FIREPROOFING PLASTER
ANSWERING YOURS DICTATED BY C. G. Shuttleworth - md

98
The sample of special fireproofing plaster which you made according to the formula in the footnote of my letter of Aug. 3 to Mr. Swytnyk of Underwriters' Laboratories Inc. has been tested and found satisfactory except for setting time, and it is a little too fast.

We understand that the U. L. Inspector will be at your plant next week to observe the running of the plaster and to place his stamp upon it for use in the fire test.

Would you please make 2 charges of this material, according to the following formula, and package in plain bags if available; if not, run it into Lite Acoustical plaster bags. Run as much into each bag as it will conveniently hold, being sure that each bag contains the same amount of plaster within normal bag weight tolerances.

Send us one bag by motor express, one gallon can by parcels post special handling and approximately 750 lbs. to Mr. B. Swytnyk, Underwriters' Laboratories Inc., Northbrook, Ill. Let us know when it goes forward.

Charge all expense to R & D 222 - J. O. No. 115.

Formula: ¹⁸⁰ 20 cu. ft. perlite - 8½ to 9½ lbs/cu. ft.
262 lbs. Stucco GR-52
76.5 lbs. Asbestos TD3
27 lbs., 5 os. Lumnite Cement - Universal Atlas or equal.
18 oz. Ultrawet D.S.
17 oz. Retarder

Let us know how much is in the bags.

Called CBS 9/13/61
act on plants - he won't do it
next - arrangements have been made
to try out next morning.

Will be
Shipped

MR REVERSKI
PLS HANDLE

28 bags
1552 #

Shipped 9/17/61
via Consolidated Truck
to Chicago, incident Motor will
deliver - 9/13/61

Called CBS 9/13/61
him of ship ment going there.

180
262
76.5
27
2.5
548.0 #/ch

1552
1568