

INTER-OFFICE MEMO **TENNECO CHEMICALS, INC.**

TO H. B. Carr . AT Burlington DATE August 21, 1969
 FROM E. L. Kanyok AT Burlington COPY TO J. C. Fisher
 SUBJECT General Tire Resin A. Stasenko
 File ✓

Quality Control has tested General Tire V-105, V-110, and V-120 preshipment samples for conformance to our specifications on 200, 225, and 250 type resins.

The results of these tests are as follows:

Properties	<u>V-105</u>	<u>Burl. 200</u>	<u>V-110</u>	<u>Burl. 225</u>	<u>V-120</u>	<u>Burl. 250</u>
Relative Viscosity	2.15	2.00-2.08	2.33	2.26-2.33	2.63	2.31-2.39
Gels	20	13 max.	19	13 max.	10	12 max.
Dry Blend	11.0	7.0-11.0	10.1	6.0-8.0	8.6	5.6-7.0
Screen						
+40	-	-	-	-	-	-
+60	Tr	0-Tr	Tr	0-Tr	Tr	0-3
+80	3	-	1	-	Tr	-
+100	35	10-40	21	40-70	22	60-90
+140	79	-	69	-	79	-
+200	94	-	89	-	94	-
Thru	6	0-5	11	0-5	6	0-5

E. L. Kanyok
 E. L. Kanyok

ELK/rjl