

RESEARCH REPORT
 Approved by Three Manufacturers in Chicago, January 1941 - June 1941

Formula - Gray (No. 1)

Percentage Formula

Working or Vat Formula

January 1941 to May 1942 2/

January 1941 to May 1942

Percent

Gals. Lbs.

35.5

Lithophone

200

Wall Special Mixing Varnish

92

Collegen Line Drier

1 1/2

100.0

Intense Drier

2

June 1942 2/

June 1942

Percent

Gals. Lbs.

35.5

Lithophone

400

Tramel Mixing Varnish

92

Collegen Line Drier

1 1/2

100.0

Intense Drier

2

Red Barn Paint (No. 702)

Percentage Formula

Working or Vat Formula

January 1941 to June 1942 2/

January 1941 to June 1942

Percent

Gals. Lbs.

95.3

Venetian Red

250

Petronite

250

Asbestine

200

100.0

Flown Soya Bean Oil

10

Raw Linseed Oil

13

Gloss Oil

24

Clean Spirits

14

Intense Drier

4

Solution

1

Cobalt Drier

2

Also from working formula.