Cnco 6.4%

CHEMICAL ANALYSIS TESTS

Ash % 52.22 N % 1.97 Type Resin 2 step Furfural Neg

CaO % Hexa on Resin 14.0% Based on Acetone Extract 14.6% Based on B-Naphthol Extract

Acetone Extract % 40.41 Color of liquor orange

Color of residue Coloring agent

B-Naphthol Extract % 38.96

Filler Content (Microscope)

On Acetone Residue

On Molded Surface Long fibre asbestos

Hot Plate Odor at 165°C

Comments on Chemical Analysis

MISCELLANEOUS TESTS

Rockwell Hardness Nigrometer Heat Distortion

Flame Resistance: Ignition Time sec. Burning Time sec.

Remarks

Modulus of Elasticity in Tension

Heat Resistance